

Sequentia® Embossed Wall Panels | FRFRJ, FX

Class A Fire-Rating per ASTM E-84

Product

Sequentia is made of fiberglass reinforced plastic. Sequentia is a durable, flexible building material and will not mold, mildew, rot or corrode. It exhibits excellent resistance to mild chemicals and moisture. The panel has a Class A rating for flame spread and smoke development when tested per ASTM E-84.

Purpose

Sequentia embossed panels are designed for interior wall finishes where a Class A, sanitary, easy-to-clean panel is desired.

Table One: Physical Properties						
Typical Values						
Property	FRFRJ FX		Test Method			
Flexural Strength	13.6 x 10³ psi	94 MPa	ASTM - D790			
Flexural Modulus	0.6 x 10 ⁶ psi	4137 MPa	ASTM - D790			
Tensile Strength	7.1 x 10 ³ psi	49 MPa	ASTM - D638			
Tensile Modulus	0.92 x 10 ⁶ psi	6343 MPa	ASTM - D638			
Barcol Hardness	40	40	ASTM - D2583			
Izod Impact	12.0 ft-lb/in notched	0.64 J/mm	ASTM - D256			
Coefficient of Linear Thermal Expansion	0.17 x 10 ^{.5} in/in/°F	31 µm/m/°C	ASTM - D696			
Water Absorption	0.32%/24hrs@77°F	0.32%/24hrs@25°F	ASTM - D570			
Surface Burning Characteristics	Class A	Class A	ASTM - E84			

Table Two: Physical Properties					
Product Code	Nominal Thickness	Finish	Color	Available Sizes	
FRFRJ			White 85		
FX (special order)	0.09" 2.3 mm	Embossed	Beige 70 Pearl Gray 48 Ivory 84 Silver 66 Colonial White 83	4'x 8' 4'x 9' 4'x 10' 4'x 12' 1.2 m x 2.4 m 1.2 m x 2.7 m 1.2 m x 3.0 m 1.2 m x 3.7 m	

Additional lengths, widths and colors available by quotation. 12,000 sq. ft. per product, weight and colors required to manufacture. Orders from different customers may be batched to obtain manufacturing minimums, however lead time may be affected.

SPECIFICATIONS

Crane Composites panels are manufactured by a continuous laminating process in lengths as required.

COMPOSITION

Reinforcement: Random chopped fiberglass. Resin Mix: Modified polyester copolymer and inorganic fillers and

pigments.

FINISHED PANEL QUALITY

- 1. Panels shall have a wear side with a pebble-like embossed finish. Color shall be uniform throughout, as specified. The backside shall be smooth. Backside imperfections which do not affect functional properties are not cause for rejection.
- 2. Physical properties shall be as set forth in Table 1.
- Dimensions shall be as specified on purchase order, subject to the following tolerances: Width: ±1/8" (±3.2 mm)
 - Length: $\pm 1/8'' (\pm 3.2 \text{ mm})$ up to 12' (3.7 m)
 - Squareness: ±1/8" (3.2 mm) in 48" (1.2 m) of width
- Product quality standards and tolerances for panel weight and thickness shall be as set forth in Crane Composites' Quality Control Procedures/Standards which are available on request.
- Panels shall be installed in accordance with manufacturer's guidelines as set forth in the Crane Composites Installation Guide (Form #6876).

CERTIFICATIONS

- 1. Meets USDA/FSIS requirements
- 2. Meets FMVSS 302 Requirements
- FRP does not support mold or mildew (per ASTM D3273 and ASTM D3274)
- Meets minimum requirements of major model building codes for Class A interior wall and ceiling finishes of flame spread ≤ 25, smoke developed 450 or less (per ASTM E-84)
- Crane Composites certifies that Sequentia (FRFRJ/FX) meets the requirements of ASTM D5319.

Classification Class A - Flame spread 0 to 25, smoke development index of 450 or less per ASTM E 84. Grade 6: 0.081 to 0.099 n. (2.06 to 2.51mm); 0.090 in. nominal (2.29mm).

Grade 6: 0.081 to 0.099 n. (2.06 to 2.51mm); 0.090 in. nominal (2.29mm). Tolerances: Width and Length: +.125 in (3.175mm) up to and including 12 ft. Squareness: +.125 in (3.175mm) Thickness: + 10% Camber: +.25 in (6.35mm)

Thickness. + 10% Camper. + .25 III (6.35

 This panel has earned GREENGUARD® SELECT Education and GREENGUARD® SELECT Healthcare Certification. (Certificate # 90154-03) www.greenguard.org



FABRICATING RECOMMENDATIONS

Note: Protect your eyes with goggles; cover your nose and mouth with a filter mask; cover exposed skin when cutting CCI panels. **Hand Fabricating:** Drilling—High speed drill bit (60° cutting angle, with

12°-15° clearance) or hole saw.

Cutting: Sheet metal shears or circular saw with reinforced carborundum or carbide-tipped blade.

Production Fabricating: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed. For irregular cuts, use die punch or band saw. **Cleaning Instructions:** Available from CCI.

STORAGE

All Crane Composites FRP products should be stored indoors.

SERVICEABLE TEMPERATURE RANGE

Panels will perform in temperatures from -40°F (-40°C) to 150°F (66° C). For use in environments beyond this range contact Crane Composites for recommendations.

LIMITATIONS

Near Heat Source: Crane Composites panels may discolor when installed behind or near any heat source which radiates temperatures exceeding 130°F (55°C), such as cookers, ovens, and deep fryers. **Uneven Surface:** Installation over uneven concrete block walls may result in areas of delamination and bulging.

NOTICE

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material does not provide an acceptable appearance, Crane Composites should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Crane Composites. Crane Composites' sole responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.

FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS

The numerical flame spread and smoke development ratings are not intended to reflect alleged hazards presented by Crane Composites products under actual fire conditions and this product has not been tested by Crane Composites except as set forth below. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test"). CRANE COMPOSITES PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced

CRANE COMPOSITES PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, FRP may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression systems, system necessary for a specific installation. We believe all information given is accurate, without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents. www.astm.org/Standards/E84.htm.

www.sequentia.com | 1.800.435.0080 | 1.815.467.8666 (fax) | salesbp@cranecomposites.com Crane Composites is the manufacturer of Glasbord, Sequentia, Sanigrid II and a variety of other fiberglass reinforced plastic (FRP) composite wall panels. Inspired by the Kemlite tradition, Crane Composites has over 55 years of experience in Commercial Building Products and is a recognized industry leader in FRP applications.



We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.