



One Product Flooring System Industrial Application



PRODUCT DESCRIPTION

JONES-BLAIR®/NEOGARD® has developed a one product easy to use system for protecting concrete floors. This two component, 100% solids epoxy, is formulated for use on damp as well as dry concrete. It can be used as a primer, patching resin, base coat, and topcoat... all in one.

IDEAL FOR

- High traffic conditions like main aisles
- Corrosion resistant environments
- Mechanical rooms
- Industrial kitchens
- Floor patching
- Maintaining floors
- Clean rooms

ADVANTAGES

- One product system
- Complies with VOC/VOS regulations
- High physical and chemical resistant properties
- High gloss
- Can be combined with several aggregates for slip resistance
- Easy to clean
- Multiple Colors

LIMITATIONS

- Not recommended for exterior applications.
- Product may fail adhesion or fish eye if oil, silicones, form release agents, or other types of contaminants are present during application.
- Do not apply if surface temperature is less than 50°F.

PACKAGING - 3 GAL KITS

Colors: 70714.....Clear 70714-01 White
 70714-02Gray 70714-03 Tan
 70714-04Dark Gray 70714-05 Tile Red
 70714-06Green 70714-11 Lt. Gray
 70714-16Black

Catalyst: 70715

Mix Ratio: 2:1 (resin:catalyst) by volume

DELIVERY, STORAGE & HANDLING

Materials shall be delivered in original sealed containers, clearly marked with supplier's name, brand name and type of material.

Recommended material storage temperature is 75°F (23.8°C). Handle products to avoid damage to container. Do not store for long periods in direct sunlight.

TECHNICAL DATA

Description	Test Method	Result
Compressive Strength	ASTM D 695	25,300 psi
Tensile Strength	ASTM D 638	3,700 psi
Elongation @ Break	ASTM D 638	25%
Flexural Modulus	ASTM D 790	57,700 psi
Shore D Hardness	ASTM D 2240	78
Adhesion	ASTM D 4541	350 psi
Taber Abrasion 1000 rev., cs17	ASTM D 4060	25 mg
Fungus & Bacteria Resistance	Mil-F-52505	No support of growth under TT-P-34
Solids by Volume	Calculated	100% (mixed)
Solids by Weight	ASTM D 4209	100% (mixed)
Viscosity	ASTM D 2196	400 cps (mixed)
Flash Point	ASTM D 3278	>200°F
VOC	EPA method 24	<5 g/L (mixed)
Shelf Life		1 year
Pot Life @ 75°F		30 minutes
Thin Film Cure		6 – 8 hours
Light Traffic Use		12 hours
Full Cure		7 days
Mix Ratio (Resin:Catalyst)		2:1 by volume

CHEMICAL RESISTANCE

Rating Key	Chemical.....	Rating
0 - No Effect	Acetic Acid 10%.....	1
1 - Stains	Ammonia 28%.....	0
2 - Blisters	Blood.....	0
	Brake Fluid.....	0-1
	Ethylene Glycol.....	0
	Isopropyl Alcohol.....	1
	Jet Fuel.....	0
	Ketchup.....	0
	Lactic Acid 85%.....	0-1
	Hydrochloric Acid 37%.....	0
	Mineral Spirit.....	0
	Motor Oil.....	0
	Mustard.....	0
	Propylene Glycol.....	0
	Skydrol.....	1
	Sulfuric Acid 50%.....	1
	Urine.....	0
	Vegetable Oil.....	0
	Vinegar.....	1
	Xylene.....	1

EXAMINATION

Concrete

- Concrete must be structurally sound
- Check for contaminants
- Look for curing compounds and form release agents
- Check with JONES-BLAIR®/NEOGARD® for more information or questions
- Floor temperature must be above 50°F (10°C) and rising
- Use degreaser detergent to remove surface oil, grease and dirt. Areas where oil or other contaminants penetrate deep into the concrete may require removal by mechanical methods.

Moisture Drive Issue

- Concrete must be dry and needs to have a minimum of 28 days cure.
- Run calcium chloride test ASTM F1869-98. Readings must not exceed 3 lbs/1000 sf/24 hrs. NOTE: Readings may vary from day to day, so the result of testing will be accurate only at the time tested.

Patching & Cracks

- Patching concrete in remedial applications is usually required. Fill voids to adjacent level with a mix of one part 70714/70715 and 4 parts oven-dry silica (40-60 mesh) by volume.
- Fill non-moving cracks with a mix of one part of 70714/70715 with two to three parts of fumed silica by volume.
- All patching and cracks shall be done after surface preparation.

EXECUTION

Preparation

- Abrade/Etch concrete surface by a mechanical procedure or by using a dilution of water and Hydrochloric Acid 20° baume at a ratio of 2:1.
- Do not let acid dry on surface. Rinse thoroughly.
- Surface to achieve a profile similar to 50 grit sand paper.

Pre-coated Concrete

- Sand thoroughly with 50 grit paper and remove all residue.
- Scrub floor with water and degreaser detergent and rinse well with water prior to application of FloorTuff™ System.

Mixing Instructions

- Read labels
- Follow mixing instructions
- Mix the color side of 70714 for three minutes before adding 70715 catalyst.
- Mixing ratio is 2 parts 70714 series to 1 part 70715 by volume.
- Mix material for three minutes
- Use a slow speed drill (600 rpm max.) and jiffy mixer.

IMPROPER MIXING AND IMPROPER MIXING RATIOS CAN RESULT IN CURING PROBLEMS

Application & Coverage Rates

- **PRIMER** - Apply in one coat at a rate of 266 sf/gal to achieve a DFT of 6 mils. Primer should always be clear. After proper mixing, dip roller in the coating, apply and roll out excess. Apply in a uniform path trying not to overlap in excess with previous paths. After 3 or 4 paths, back roll the surface for uniform appearance and until you achieve proper thickness. Within 36 hours of application of primer, topcoat must be applied. If topcoat cannot be applied within 36 hours, lightly sand the entire surface to develop a profile. Remove imperfections and/or dust.
- **TOPCOAT** - Apply one coat of clear or color topcoat at a rate of 160 sf/gal to achieve 10 mils DFT. After proper mixing, dip roller in the topcoat, apply and roll out excess. Apply in a uniform path trying not to overlap in excess with previous paths. After 3 or 4 paths, back roll the surface for uniform appearance or to achieve proper thickness.
- **OPTIONAL COAT** - For custom color or UV stability, use Acrylithane HS2

APPLICATION TOOLS

- Safety is first. Use protective clothing, safety glasses and post warning signs.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. Applicator is an independent contractor of, and should under no circumstances be viewed as an employee or agent of, the JONES-BLAIR®/NEOGARD®. 111406FloorTuffJBN.indd

JONES-BLAIR®/NEOGARD®