

POLYFLEX® SA P

PRODUCT DESCRIPTION

Polyflex SA P membranes are premium, self-adhered plastomeric roofing products, manufactured using patented ADESO® Dual-Compound Self-Adhesive technology, whereby a "true" APP polymer modified asphalt compound is applied on the top layer and an aggressive self-adhesive compound is applied on the bottom layer. Polyflex SA P membranes are built with a high performance reinforced polyester mat to ensure excellent dimensional stability.

Polyflex SA P membranes are finished with granules on the top surface and feature patented FASTLap® for granule free roll ends, as well as SEALLap®, a factory applied adhesive treatment at the membrane overlap. Each of these patented features provide for greater ease of application, as well as improved product performance.

USES

- Designed for applications where using a propane torch is undesirable or prohibited
- Applications include new construction, re-roofing and BUR repair installation
- As a flashing membrane in all applicable specifications

FEATURES AND BENEFITS

- Excellent long-term adhesion and application to multiple substrates and base plies
- Exceptional physical properties and long-term weathering performance
- UV stabilized long lasting granule surfacing in multiple colors

TECHNICAL DESCRIPTION

TEST METHOD	PROPERTY	TYPICAL VALUE
ASTM D5147	Thickness, typical, mm (mils)	3.5 (140)
ASTM D5147	Peak Load @ 23+/-2°C (73.4+/-3.6°F), MD and XMD, min, kN/m (lbf/in.)	8.8 (50)
ASTM D5147	Elongation @ 23+/-2°C (73.4+/-3.6°F), MD and XMD, min (%)	23
ASTM D5147	Tear Strength @ 23+/-2°C (73.4+/-3.6°F), min, N (lbf)	311 (70)
ASTM D5147	Low Temperature Flexibility, max, °C (°F)	0 (32)
ASTM D5147	Granule Embedment, max, g	2
ASTM D1970	Adhesion to Plywood @ 40°F, min, lbf/ft width	2.0
ASTM D1970	Adhesion to Plywood @ 75°F, min, lbf/ft width	12.0
ASTM D1970	Sealability around nail	pass
ASTM D1970	Waterproof integrity after low temp flexibility	pass
ASTM D1970	Waterproof integrity of lap seam	pass

AVAILABLE COLORS

Top surface granule protection is available in a variety of colors such as:

Black Buff Chestnut Grey Slate Oak
White Red Blend Pine Green Heather Blend Weatherwood



PRODUCT DATA

Coverage (Nominal) 100 sq ft
Weight (Approx) 90 lbs
Roll Size 32'10" x 39 3/8" (10m x 1m)
Rolls/Pallet.....20

APPLICABLE STANDARDS

- ASTM D 6222
- Miami Dade Code Compliance
- UL Classified for use in class A, B or C roofs, as listed the latest UL "Roofing Materials and Systems Directory"
- ICC ESR-2018
- Florida Building Code
- TDI



PRODUCT WARRANTY

Polyglass USA, Inc. commercial roofing membranes can be backed with a manufacturer's warranty for up to 20 years when used as part of an approved, multi-ply roofing system. Please see your Polyglass USA, Inc. Sales or Technical Representative for specifications and details.



1-800-222-9782

www.polyglass.com

POLYFLEX® SA P

APPLICATION INSTRUCTIONS

Polyflex SA P is intended to be used as a cap sheet for new or re-roof applications as part of a multi-ply system when applied to acceptable insulations and/or coverboards for commercial and residential structures. Polyflex SA P may also be applied directly to approved wood deck substrates of non-occupied spaces such as carports, sheds, canopies, etc.

- Apply only when the weather and forecast is dry and the ambient air temperature and substrate is 40°F (5°C) and rising.
- Apply over clean, dry, dust and debris-free substrates. Prime concrete decks prior to application with PG 100 Asphalt Primer.
- When re-roofing, remove all prior roofing materials down to a clean debris-free substrate and properly close-off all abandoned roof penetrations.
- Concrete or steel decks shall be designed with proper expansion devices.
- Wood decks shall have all joints blocked and properly supported.
- Ensure the installation of Polyflex SA P does not prevent the ventilation of existing construction.
- Do not apply over shingles or other granulated surface.
- While installing Polyflex SA P:
 1. Start at the low point of the roof.
 2. Unroll the material and allow to relax.
 3. Start by removing the first 18-24" of release film.
 4. Press the membrane into place with firm and even pressure. Roll the edges with a silicone hand roller to ensure complete adhesion.
 5. Gradually remove the remaining release film applying pressure from the center to the edges as you go.
 6. Position successive rolls providing a minimum 6" end lap and 4" side lap. Laps can be sealed for additional water tightness with a hot air welder.
 7. After installation of the entire roof surface, roll with an 80# split-face linoleum roller. Take care on sloped roofs by securing the roller and applicator with the appropriate safety equipment.
- Details and flashing may be installed using Polyflex SA P with a hot air welder or with PG 500 Roof Cement. Check project details for proper installation requirements.

POLYGLASS U.S.A., INC. MANUFACTURING FACILITIES

- Fernley, NV
- Hazleton, PA
- Winter Haven, FL

CORPORATE HEADQUARTERS

Polyglass U.S.A., Inc.
1111 West Newport Center Drive
Deerfield Beach, FL 33442
www.polyglass.com

General Line: (888) 410-1375
(954) 233-1330

Customer Service: (800) 222-9782
Technical Service: (866) 802-8017

Questions? technical@polyglass.com

Product Disclaimer: Unless otherwise incorporated into or part of a supplemental manufacturer's warranty, Polyglass warrants its product(s) against manufacturing defects in its product that directly results in leakage for a period of 5 years.

Refer to material safety data sheet (MSDS) for specific data and handling of our products. All data furnished refers to standard production and is given in good faith within the applicable manufacturing and testing tolerances.

Polyglass U.S.A., Inc., reserves the right to improve and change its products at any time without prior notice. Polyglass U.S.A., Inc. cannot be held responsible for the use of its products under conditions beyond its own control.

For most current product data and warranty information, visit www.polyglass.com



1-800-222-9782
www.polyglass.com