

Sure Klean® Concrete Brick Cleaner Cleaning Specification

Specifier Note: The information provided below is intended to guide the Architect in developing specifications for products manufactured by PROSOCO, Inc. and should not be viewed as a complete source of information about the product(s). The Architect should always refer to the Product Data Sheet and MSDS for additional recommendations and for safety information

Specifier Note: Paragraph below is for PART 1 GENERAL, Quality Assurance.

Test Area

Test a minimum 4 ft. by 4 ft. area on each type of masonry. Use manufacturer's application instructions. Let the test panel dry 3 to 7 days before inspection. Keep test panels available for comparison throughout the cleaning project.

Specifier Note: Paragraphs below are for PART 2 PRODUCTS, Manufacturers and Products.

Manufacturer: PROSOCO, Inc., 3741 Greenway Circle, Lawrence, KS 66046. Phone: (800) 255-4255; Fax: (785) 830-9797. E-mail: CustomerCare@prosoco.com

Product Description

Sure Klean® Concrete Brick Cleaner removes common construction and atmospheric staining from concrete brick and other architectural concrete surfaces. This general-purpose, non-etching acidic cleaner removes mortar smears, rust, mud, atmospheric dirt and other stains without altering the surface texture. Concrete Brick Cleaner adds depth to colors and brightens white matrices and exposed aggregate.

Technical Data

FORM: Clear liquid
SPECIFIC GRAVITY: 1.129
TOTAL SOLIDS: NA
pH: 0.976 @ 1:2 dilution
WT./GAL: 9.39 lbs.
FLASH POINT: NA
FREEZE POINT: 19.8°F (-6.8°C)

Limitations

- May damage polished masonry, some nonmasonry and acid-sensitive surfaces.

Specifier Note: Paragraphs below are for PART 3 EXECUTION, Installation.

Application

Before applying, read "Preparation" and "Safety Information" sections in the Manufacturer's Product Data Sheet for Concrete Brick Cleaner.

Dilute 1 part concentrate to 3 parts water. Always pour COLD water into empty bucket first, then carefully add product. NEVER USE HOT WATER. Handle in polypropylene buckets only.

Application Instructions

1. Always prewet surface thoroughly with fresh water. When cleaning vertical surfaces, keep lower areas wet to avoid streaks.
2. Working from the bottom to the top, apply diluted Concrete Brick Cleaner directly to surface with masonry brush or low-pressure spray.
3. Let the cleaner stay on the surface for 3-5 minutes or until stains have disappeared.

4. Reapply cleaner and rinse thoroughly with fresh water, rinsing from the bottom to the top to remove all residues. The best combination of rinsing pressure and water volume is provided by masonry washing equipment generating 400-1000 psi with a water flow rate of 6-8 gallons per minute delivered through a 15-45 degree fan spray tip. Equipment should be adjustable to reduce water flow rate and rinsing pressure as required for controlled cleaning of more sensitive surfaces. See also "Equipment" section of the Product Data Sheet. If pressure rinsing equipment is not available, brush the surface while rinsing with clean water.

NOTE: Multiple applications may etch acid-sensitive surfaces.