

Sikagard® 62

High-build, protective, solvent-free, colored epoxy coating

Description	High-build, protective, solvent-free, colored epoxy coating.
Where to Use	Use as a high build, corrosion-resistant, protective coating, as a protective lining for secondary containment structures or as a seamless flooring system.
Advantages	<ul style="list-style-type: none"> ■ Exceptional tensile strength. ■ Good chemical resistance for long-term protection. ■ Convenient A:B = 1:1 mixing ratio. ■ Easy, paint-like viscosity. ■ Available in 3 standard colors: gray, red, and tan. ■ Excellent bonding to all common structural substrates. ■ Super abrasion resistance for long-term wear. ■ Sikagard® 62 gray, after cure, is approved for contact with potable water. ■ Material is USDA certifiable.
Coverage	Approximately 150-250 ft. ² /gal. depending on condition of substrate.
Packaging	4 gal. units; 1 qt. units, 12/case.

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	2 years in original, unopened containers.		
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-75°F (18°-24°C) before using.		
Color	Gray, red, tan.		
Mixing Ratio	Component 'A' : Component 'B'=1:1 by volume.		
Viscosity (Mixed)	Approximately 3,500 cps.		
Pot Life	Approximately 35 to 40 minutes. (60 gram mass).		
Tack-Free Time	Approximately 4 hours.		
Open Time	Light foot traffic: 5-7 hours. Rubber-wheel traffic: 8-10 hours.		
Immersion and Chemical Exposure	Minimum cure: 3 days		
Tensile Properties (ASTM D-638)			
14 day	Tensile Strength	5,400 psi (37.3 MPa)	
	Elongation at Break	2.7 %	
Abrasion (ASTM D-1044) (Taber Abrader)			
7 day	Weight loss, 1,000 cycles (H-22 wheel, 1,000 gm weight)	0.61 gm	
Abrasion Resistance (ASTM D-968)			
14 day	Abrasion Coefficient	51 liters/mil.	
Adhesion (ASTM D-3359)			
1 day	Adhesion Classification	4A	
Water Absorption (ASTM D-570)			
7 day	(24 hour immersion)	0.1%	



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

How to Use

Surface Preparation	<p>Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes and any other contaminants.</p> <p>Preparation Work: Concrete - Should be cleaned and prepared to achieve a laitance and contaminant free, open textured surface by blastcleaning or equivalent mechanical means.</p> <p>Steel - Should be cleaned and prepared thoroughly by blastcleaning.</p>
Mixing	<p>Pre-mix each component. Proportion equal parts by volume of Components 'A' and 'B' into a clean mixing container. Mix with a low-speed (400-600 rpm) drill using a Sika paddle for 3 minutes, until uniform in color.</p>
Application	<p>Apply coating using high-quality roller, brush or spray. Two coats are recommended. Apply second coat as soon as the first coat is tack-free and the traffic of application will not damage the first coat. The second coat, however, must be applied within 48 hours since a longer delay will require additional surface preparation.</p> <p>Do not spray with slip resistant granules mixed into the coating. For use as a seamless flooring system, consult Technical Service.</p>
Limitations	<ul style="list-style-type: none"> ■ Minimum substrate and ambient temperature for application 50°F (10°C). ■ Maximum moisture content of concrete substrate by weight when measured with a Tramex CME or CMExpert type concrete moisture meter is 4%. ■ Do not apply over wet, glistening surface. ■ Material is a vapor barrier after cure. ■ Do not apply to porous surfaces exhibiting moisture-vapor transmission during the application. Consult Technical Service. ■ Minimum age of concrete prior to application is 21-28 days, depending on curing and drying conditions. ■ Do not apply to exterior, on-grade substrates. ■ Use oven-dried aggregate only. ■ Do not thin with solvents. ■ Not an aesthetic product. Color may alter due to variations in lighting and/or UV exposure. ■ On 'green or 'damp' concrete, EpoCem can be used as a pore filler to reduce vapor drive and potential osmotic blistering.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikagard are registered trademarks.
Printed in Canada.

