

Sikadur 51 NS

Flexible epoxy control-joint sealer/adhesive

Construction

Description	Sikadur 51 NS is a 2-component, non-sagging, solvent-free, moisture-tolerant, flexible epoxy control joint sealer and adhesive.
Where to Use	<ul style="list-style-type: none">■ Use to fill vertical and overhead non-moving, saw-cut construction control joints and cracks.■ Use as a flexible adhesive.
Advantages	<ul style="list-style-type: none">■ 2 to 1 ratio ensures easy mixing, easy handling.■ An adhesive with excellent flexibility.■ Excellent durability.■ Conforms to ACI 302.1R (4.10-Joint Materials).■ Shock-absorbent cure.■ Prevents deterioration of control-joint edges.■ Use as a security sealant.■ Use as a pick proof sealant.
Coverage	1 gal. will yield 231 cu. in. or will fill 102 ft. of 1/8 in. wide x 1.5 in. deep joint.
Packaging	3 gallon units.

Typical Data *Material and curing conditions @ 73°F (23°C) and 50% R.H.*

Shelf Life	2 years in original, unopened containers		
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-85° F (18°-29°C) before using.		
Color	Concrete gray		
Mixing Ratio	Component 'A': Component 'B' = 2:1 by volume.		
Viscosity	Comp. 'A'	300,000-350,000 cps	
	Comp. 'B'	29,000-31,000 cps	
	Mixed	Non-sag paste	
Pot Life	1-1.5 hours		
Tack-Free Time	7-8 hours.		
Tensile Properties (ASTM D-638)			
14 days	Tensile Strength	650 psi (3.9 MPa)	
	Elongation at Break	80%	
	Modulus of Elasticity	1,800 psi (12.4 MPa)	
	Tensile stress at % elongation	2.5%	50 psi (0.35 MPa)
		5%	90 psi (0.62 MPa)
		10%	160 psi (1.10 MPa)
Tear Resistance (ASTM D-624)	14 days	110 lb./in. (19.4 N/mm)	
Hardness (ASTM D-2240)	28 days	(Shore A) 75-80	(Shore D) 30-40

How to Use

Surface Preparation Substrate must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, laitance, grease, curing compounds, impregnations, waxes, foreign particles, disintegrated materials, etc., by mechanical means (i.e. sandblasting, high pressure waterblasting).

The Sika logo consists of the word "Sika" in a bold, italicized, sans-serif font, with a registered trademark symbol (®) to its upper right. The text is white and is set against a red, upward-pointing triangle.

Mixing	Pre-mix each component. It is critical to accurately proportion 2 parts Component 'A' and 1 part Component 'B' by volume into a clean pail. Mix thoroughly for 3 minutes with a Sika Paddle on a low-speed (400-600 rpm) drill until uniform in color. Mix only that quantity which can be used within pot life.
Application	For vertical or overhead applications, gun Sikadur 51 NS into construction/control joints and cracks with caulking gun, pressure extruder, or other suitable methods. Be sure to maintain steady pressure and steady flow of material, filling entire joint in a single application. Take care to eliminate overlapping as this may cause bubbling within the material. For use as a flexible adhesive, consult Sika Technical Service at 800-933-SIKA.
Limitations	<ul style="list-style-type: none"> ■ Do not thin Sikadur 51 NS. Addition of solvents may prevent proper cure. ■ Substrate temperature should be 40°F (4°C) minimum and rising. ■ For best results, materials should be maintained between 65°-85°F (18°-29°C) during application ■ Do not apply through standing water. ■ Minimum age of concrete is 28 days. ■ Materials are vapor barriers after cure. ■ Concrete or masonry must be tested for water-vapor transmission prior to application. ■ Not designed for use under constant immersion in water or other liquids. ■ Do not use in expansion (moving) joints. ■ For application in non-moving joints only. ■ The ultimate performance of Sikadur 51 NS depends upon many factors, [i.e., proper joint design, thermally stable areas, (concrete slab), etc.]. ■ For applications other than sealing of control or construction joints, consult Sika Technical Service at 800-933-SIKA.
Caution	<p>Component 'A' - Sensitizer; Irritant - Contains epoxy resins. May cause skin/respiratory irritation. Prolonged and/or repeated contact with skin may cause allergic reaction/sensitization. High concentrations of vapor may cause respiratory irritation. Avoid eye contact. Harmful if swallowed.</p> <p>Component 'B' - Corrosive; Sensitizer - Contains amines and crystalline silica. Contact with skin and eyes can cause severe burns. Respiratory irritant. Possible sensitization/allergic reaction with prolonged exposure. High concentrations of vapor may cause respiratory irritation. If product is sanded or abraded after curing, crystalline silica dust can be inhaled and cause delay lung injury (silicosis). Harmful if swallowed.</p> <p>Intentional misuse by deliberate concentration and inhalation of vapors may be harmful or fatal.</p>
First Aid	Eyes -rinse thoroughly with water for 15 minutes; remove contaminated clothing. Skin - wash skin with soap and water. Wash clothing before reuse. Inhalation - remove person to fresh air. Ingestion - Do not induce vomiting. Contact a physician. In all cases, contact a physician if symptoms persist.
Handling & Storage	Avoid direct contact with eyes and skin. Wear chemical resistant gloves/goggles/clothing. Avoid breathing vapors. Use with adequate general and local ventilation. In the absence of adequate ventilation, use a properly fitted NIOSH respirator. Wash thoroughly after handling product. Remove contaminated clothing and launder before reuse. Store product in closed container in cool, dry, well ventilated place.
Clean Up	Avoid contact. Uncured material can be removed with soap and water or solvent. Follow solvent manufacturer's instructions for use and warnings. Cured product can only be removed mechanically. Consult a physi-

KEEP CONTAINER TIGHTLY CLOSED
NOT FOR INTERNAL CONSUMPTION

KEEP OUT OF REACH OF CHILDREN
FOR INDUSTRIAL USE ONLY

CONSULT MATERIAL SAFETY DATA SHEET FOR MORE INFORMATION

Sika warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Technical Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor.

NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS.

Visit our website at www.sikaconstruction.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Quality Certification Numbers: Lyndhurst: FM 69711 (ISO 9000), FM 70421 (QS 9000), Marion: FM 69715, Kansas City: FM 69107, Santa Fe Springs: FM 69408

Sika and Sikadur are registered trademarks. Made in USA. Printed in USA.

