

## **#901 ELASTOMERIC ROOF COATING**

**TROPICAL ROOFING PRODUCTS' #901 ELASTOMERIC ROOF COATING** is a good quality, Energy Star® rated, highly reflective elastomeric polymer latex based roof coating that forms a seamless and flexible layer of protection for your roof. This durable coating is designed to seal and dramatically reduce the surface temperatures. #901 Elastomeric Roof Coating is formulated to provide a tough, durable weather resistant coating. This flexible, fast drying, elastomeric coating adheres readily to most roofing substrates and provides a protective and reflective finish that will keep the sun's damaging rays from prematurely aging your roof, while keeping the substrate temperatures substantially lower to alleviate stress on the membrane. The flexibility of #901 Elastomeric Roof Coating gives the coating the ability to expand and contract with the movement on the roof.

**PREPARATION**: Surface must be clean, dry, and free of moisture both on and beneath the surface. Pressure wash roof thoroughly to remove as much dust, dirt, and debris as possible. After careful inspection of entire roof, repair all holes, cracks, tears, or breaks with reinforcing fabric and #950 Eternamastic. #950 Eternamastic repairs can usually be coated within 24 hours. Coat newly applied asphalt emulsion as soon as the emulsion can take foot traffic without scuffing the surface, normally 7-10 days.

**APPLICATION:** Apply on warm, sunny days, preferably in the morning hours to provide maximum cure time. #901 can be applied to a dry or slightly damp, but not wet, surface. Water must be swept out of all puddles prior to application of #901. Stir #901 thoroughly before application to achieve a uniform consistency. Apply with a heavyduty paint roller or heavy-duty spray equipment. When applied with roller or brush, strokes should be kept in one direction. Apply second coat perpendicular to the first. Allow at least 4 hours between coats and 24–48 hours for full cure, dependent upon weather conditions.

**COVERAGE:** Apply at a minimum rate of 1-1.5 gallons per 100 sq. feet. dependent upon roof porosity. Two coats are required.

**PRECAUTIONS:** DO NOT APPLY IF TEMPERATURE IS BELOW 50° F OR ABOVE 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48–72 HOURS. DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur. This coating is not recommended for areas with inadequate drainage (ponding water), over gravel, over walking decks, or old roofs that are too brittle and dry. DO NOT APPLY TO FLAT SURFACES WITH POOR DRAINAGE OR WHERE PONDING WATER WILL EXIST.

**CLEANUP:** Clean tools with mineral spirits or paint thinner.

## **CAUTION! COMBUSTIBLE!**

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

CRRC PRODUCT ID = 0656-0003
MAXIMUM V.O.C = 48 G/L
SOLAR REFLECTIVE, D.O.E. — .88
WEIGHT — 10.3 LBS. PER GAL
VOLUME SOLIDS — 42%
WEIGHT SOLIDS — 56%





