



#972 SEBS ELASTOMERIC ROOF COATING

TROPICAL ROOFING PRODUCTS' #972 SEBS ELASTOMERIC ROOF COATING is a single component block copolymer elastomeric fluid applied coating. The coating needs no intermixing, is easy to apply, and has excellent surface appearance. #972 SEBS Elastomeric Coating provides excellent elongation properties, cold weather pliability, chemical, weather, and water resistance. #972 SEBS Elastomeric Coating may be applied to metal, steel, concrete, aluminum, brick, polyurethane, wood, and fiberglass surfaces. The coating also can be used to re-coat existing acrylic or polyurethane coatings and most painted surfaces. #972 SEBS Elastomeric Coating may be applied to APP, SBS, and BUR roofing.

PREPARATION: All surfaces to be coated must be clean, dry, and free from dirt, oil, grease, and rust. Newly poured concrete must cure a minimum of 30 days prior to application of #972. Metal and wood must be primed with Elastomeric Primer at the rate of 1/2 to 3/4 gallon per 100 square feet.

APPLICATION: Recommended application for #972 SEBS Elastomeric Coating is by brush, spray, or roller. Apply two gallons per 100 square feet in two applications (one gallon of base and one gallon of top coating). Allow base coat (Stain Blocker) to cure thoroughly prior to application of the finish coat. Curing will take 12 to 24 hours dependent upon ambient temperatures and humidity.

PRECAUTIONS: DO NOT APPLY IF TEMPERATURE IS BELOW 50° F OR ABOVE 110°F. DO NOT APPLY IF THERE IS A THREAT OF RAIN OR DEW WITHIN 48-72 HOURS. DO NOT ALLOW TO FREEZE. DO NOT THIN. DO NOT HEAT CONTAINER or store at temperatures greater than 120°F. Be sure the lid is tight and the pail is secured when transporting this product. Do not allow pail to tumble as this may loosen the lid and allow leakage or spillage to occur. This coating is not recommended for areas with inadequate drainage (ponding water), over gravel, over walking decks, or old roofs that are too brittle and dry. DO NOT APPLY TO FLAT SURFACES WITH POOR DRAINAGE OR WHERE PONDING WATER WILL EXIST.

CLEANUP: Clean tools with mineral spirits or paint thinner.

CAUTION! COMBUSTIBLE!

KEEP OUT OF REACH OF CHILDREN. Close container after each use. DO NOT TAKE INTERNALLY! If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY!

MAXIMUM V.O.C = 550 G/L
ELONGATION – 875%
PERMEANCE – 1.3
VISCOSITY @ 770 F, KU– 115 +/- 5
DENSITY(WPG) – 9.5 +/- .2
CURE TIME – AVERAGE: 12-24 HOURS

FLORIDA
1904 SW 31ST AVE
HALLANDALE, FL 33009
800.432.2855

CALIFORNIA
14435 MACAW STREET
LA MIRADA, CA 90638
877.827.2622

TEXAS
1225 BRAI DRIVE
PORT ARTHUR, TX 77640
866.727.0091