

# TRI-BUILT® #15 Asphalt Felt – ASTM D 226

## PRODUCT DESCRIPTION:

TRI-BUILT® #15 ASTM D 226 is a widely accepted underlayment product that is manufactured from superior quality organic felt that is saturated with asphalt. Line markings are placed on the top surface at 2", 8 ½", 11 5/16", and 17" from each side of the sheet.

## PRODUCT USE:

TRI-BUILT® #15 – ASTM D 226 underlayment is applied over the roofing deck before installation of asphalt shingles. This product is highly recommended as an underlayment for architectural shingles and is not recommended for 20 year 3 tab shingles.

## TECHNICAL DATA:

### ASTM D 226 Type I

Width of roll	36"
Roof coverage per roll	432 sq. ft.
Mass of saturated felt roll	11.5 lbs. / 100 ft. sq.
Mass of asphalt saturant	6.2 lbs. / 100 ft. sq.
Mass of desaturated felt	5.2 lbs. / 100 ft. sq.
Max ash	10%
Average (min.) breaking strength	
Machine direction	30 lbf/in
Cross direction	15 lbf/in
Pliability at 77 ° F when bend 90°	½" radius
Max. loss on heating at 221° F	4%
<b>PACKAGING:</b>	
Pallet size	42" x 48"
Rolls per pallet	25 - 4 sq. rolls
Pallets per truck	36