

TRIBUILT® #15 Asphalt Felt – ASTM D 4869

PRODUCT DESCRIPTION:

TRIBUILT® #15 – ASTM D 4869 is a widely accepted underlayment product that is manufactured from organic felt and is saturated with asphalt.

PRODUCT USE:

TRIBUILT® #15 – ASTM D 4869 underlayment is applied over the roofing deck before installation of asphalt shingles. It is recommended for use with 20 and 25 year asphalt shingles.

TECHNICAL DATA:

ASTM D 4869 Type I

Width of roll	36"
Roof coverage per roll	432 sq. ft.
Mass of saturated felt roll	8.0 lbs. / 100 ft. sq.
Mass of asphalt saturant	4.0 lbs. / 100 ft. sq.
Mass of desaturated felt	4.0 lbs. / 100 ft. sq.
Saturation by weight (min)	100%
Saturation efficiency (min) by weight	75%
Breaking strength at 77F (min)	
Machine direction	30 lbf/in
Cross direction	15 lbf/in
Pass 4 hour liquid transmission water test	YES
Pliability at 77F when bend 90 degrees	½" radius

PACKAGING:

Pallet size	42" x 42"
Rolls per pallet	30 - 4 sq. rolls
Pallets per truck	44

Note: Special runs of 400 sq. ft. rolls do not meet ASTM 4869 Type I