

TRI-BUILT® #30 Asphalt Felt – ASTM D 226

PRODUCT DESCRIPTION:

TRI-BUILT® #30 ASTM D 226 is a widely accepted underlayment product that is manufactured from superior quality organic felt that is saturated with asphalt. Line markings are placed on the top surface at 2", 8 ½", 11 5/16", and 17" from each side of the sheet.

PRODUCT USE:

TRI-BUILT® #30 – ASTM D 226

underlayment is applied over the roofing deck before installation of asphalt shingles. This product is highly recommended as an underlayment for architectural shingles and is not recommended for 20 year 3 tab shingles.

TECHNICAL DATA:

ASTM D 226 Type II

Width of roll	36"
Roof coverage per roll	216 sq ft
Mass of saturated felt roll	26 lbs./ 100 ft. sq.
Mass of asphalt saturant	15 lbs. / 100 ft. sq.
Mass of desaturated felt	10 lbs. / 100 ft. sq.
Max ash	10%
Average (min.) breaking strength	
Machine direction	40 lbf/in
Cross direction	20 lbf/in
Pliability at 77 ° F when bend 90°	¾" radius
Max. loss on heating at 221° F	4%
PACKAGING:	
Pallet size	42" x 48"
Rolls per pallet	25 - 2 square rolls
Pallets per truck	36