

Monolithic Membrane 7800 Primer LS

GENERAL DESCRIPTION

A low solvent, SBS polymer modified, asphalt primer. Tough, flexible, adhesive and cohesive film is easy to apply and complies with V.O.C. regulations. Elastomeric - moves with substrate.

BASIC USE

The MM 7800 Primer LS is used to prime all substrate surfaces to receive Hydrotech's Monolithic Membrane 7800 including concrete, wood and metal.

ADVANTAGES

- Easy to apply.
- Tough, flexible, adhesive and cohesive film.
- Elastometric - moves with substrate
- Complies with current V.O.C. regulations.

APPLICATION

- All surfaces to be treated with MM7800 Primer must be clean, dry and free from dust, dirt, rust, grease and oil.
- The MM7800 Primer may be brushed, rolled, or sprayed to provide a thin, uniform, film at a rate of 1 gallon per 100 square feet.
- The MM7800 Primer must be allowed sufficient time to thoroughly dry. Recommended: 2 - 4 hours @ 70 degrees F and 24 hours @ 40 degrees F. Cure time may increase at lower temperatures.
- The MM7800 Primer must not be thinned.

CAUTIONS

Do not smoke or use near fire, flame or electrical sparks. If interior areas are to be coated, arrange for adequate ventilation. Avoid breathing solvent fumes and prolonged contact with skin. See MSDS for further information.

LEED® INFORMATION

| | Credit 4 | Credit 5 |
|--------------------------------|----------|-----------|
| Recycled Content (% by weight) | 0 | |
| Manufacture Location | | Clark, NJ |
| Extraction/Harvesting Location | | Clark, NJ |
| VOC Content (g/L) | | <250 |

This information is intended only for general conceptual purposes. It is based on data and knowledge considered to be true and correct. It is offered for the user's consideration, investigation and verification and is not intended to substitute for the advice provided by appropriate professionals. Hydrotech assumes no liability for the use of this information. The determination of the suitability and applicability of this information is the sole responsibility of the user.