



COMPLIANCE: CRRC. Title 24. Energy Star. ASBESTOS FREE.

DESCRIPTION: APOC® 247 Sun-Shield White Reflective Roof Coating is a flexible, white acrylic roof coating. This product resists cracking and peeling while extending the life of the roofing substrate. It expands and contracts with the roofs movements to resist damage. This coating also provides a protective barrier which reflects the suns heat and destructive UV rays. In turn, this helps to cool surfaces and leads to a reduction of roof temperatures. APOC 247 expands and contracts up to 275% and provides good adhesion to a variety of roofing substrates. Note: Make all repairs before applying coating.

PREPARATION: All surfaces must be dry and free of dust, dirt, oil, loose granules, gravel, peeling paint and all other foreign matter. Rusty metal must be cleaned with a wire brush and primed with APOC 291 before application of this product. Surfaces with mildew growth or stains must be cleaned with a bleach solution (2 parts water to one part bleach) prior to applying this product. Rinse thoroughly. Pressure washing entire surface is recommended for best results (use only a wide fan tip - do not allow stream to tear into roof surface). Repair all leaks and cracks with Polyester Reinforcing Fabric and APOC 264 White Roof Patch or APOC Incredible™ Fleece Top™ Tape where appropriate. Allow to cure 24 - 36 hours before application of roof coating. Surfaces previously coated with aluminum, asphalt or tar should be allowed to cure for a minimum of one summer season prior to coating with this product. Do not heat or thin. DO NOT APPLY WHEN HEAVY DEW OR RAIN IS EXPECTED WITHIN 2 - 4 HOURS.

FOR BEST RESULTS: Apply in accordance with APOC Guide Specifications found at www.apoc.com.

APPLICATION: For exterior use only. Protective clothing, gloves, and eyewear should be used during application of this product. Always apply on a clear, warm sunny day. Apply in morning hours to allow maximum cure time. Application should be completed a minimum of 4 hours prior to sunset. Temperatures must be above 55 °F (for 24 hours) and rising, but not above 110 °F. Apply with a 3/4" nap exterior paint roller or professional airless sprayer. First, apply one coat over all seams and joints. Allow to cure for one hour or until dry, then apply two (2) uniform coats over entire surface, avoiding excessive rolling. Two full coats are needed for all applications. Dries for recoat in 4 hours and fully cures in 24 - 36 hours at 70 °F & 50% relative humidity. Higher humidity, thicker films, poor air flow and lower temperatures will increase dry times. Coverage rate is 1 1/2 gallons per square, per coat. Two coats are required for a total application of 3 gallons per square.

SPRAY INFO: 2000 - 3000 PSI, .030 - .041 Tip Size, 1 - 3 GPM.

NOTE: If roof becomes hot (over 100 °F) during application, lightly mist roof surface with water spray to prevent coating from drying too fast. Remove any excess or puddling water prior to coating. If roof surfaces become soiled as they age, due to the elements, Elastomeric can be cleaned with a mild water and bleach solution. Excessive scrubbing should be avoided. If color tinting is desired, a typical addition of 3 - 4 ounces per gallon of Universal colorant can be added, which will result in light pastel colors. Color tinting will disclaim warranty.

CLEAN-UP: Clean tools with soap and water.

©2009 Gardner-Gibson, Inc.
Manufactured by / Fabricado por:
Gardner-Gibson, Inc.
P.O. Box 5449, Tampa, FL 33675

See SDS for more info

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	11.42 lbs.
Solids by Weight*	62%
Solids by Volume*	50%
Viscosity (ASTM D2697)	110 - 140 ku
Elongation (ASTM D562)	275%
Tensile Strength (ASTM D2370)	250 psi
Reflectivity (ASTM C1549)	.87 (Initial) .76 (3 yr.)
LEED Emissivity (ASTM E408)	.93 (Initial)
CRRC Emissivity (ASTM C1371)	.90 (Initial) .90 (3 yr.)
LEED SRI (Oak Ridge Calculator)	110
Permeability (ASTM D1653)	< 20 perms
Adhesion to Polyurethane Foam	good
Consistency	Brush, Spray or Roller
Skin Time (50% Relative Humidity, 70 °F)	4 hours
Full Cure (50% Relative Humidity, 70 °F)	24 - 36 hours
Application Temperatures	55 °F and Rising
Flammability	N/A (water-based)
Clean-up Tools	Soap & Warm Water

NOTE: Percentages listed are + or - 5%

Approx. Shipping Weights: (Note: All approx. weights include container)

5 gallons (18.9L)	62 lbs.
55 drums (208.2L)	672 lbs.
275 gallon tote (1,039.5L)	3,200 lbs.

VOC: <50 g/L (regulatory)

HANDLING PRECAUTIONS: Product safety information required for safe use is not included. Before handling, read product safety data sheets and container labels for safe use and for physical and health hazard information. Safety Data Sheets are available on the APOC website at www.apoc.com. You can also obtain a copy from your local APOC Distributor or APOC sales representative.

LIMITED WARRANTY AND DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact APOC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with APOC warranty procedures and program.

For limited warranty and disclaimer information, visit our website at: www.apoc.com/productwarrantyinfo.