

ETERNA-PATCH™ WHITE THERMOPLASTIC PATCH DATA SHEET

COMPLIANCE: Exceeds performance requirements of ASTM D4479, ASTM D6511. MIAMI-DADE COUNTY APPROVED. ASBESTOS FREE.

DESCRIPTION: APOC[®] **505** Eterna-Patch[™] is a white, thermoplastic, liquid rubber patching compound. It is manufactured using a select blend of high performance rubber and solvent resulting in unmatched durability and long term life. APOC[®] **505** Eterna-Patch[™] forms a permanent rubber repair that expands and contracts with roof movement while remaining flexible and watertight. This product is excellent for application to metal roofs, concrete and some single ply membranes. APOC[®] **505** is ideal for metal seams, fasteners and areas with movement.

PREPARATION: All surfaces must be dry and free of dust, dirt, oil, loose granules, gravel, peeling paint and all other foreign matter. Rusty metal should be cleaned with a wire brush and primed with APOC® 250 Metal Primer before application of this product. Surfaces with mildew growth or stains must be cleaned with a bleach solution (2 parts water to one part bleach) prior to applying this product. Rinse thoroughly. Pressure washing entire surface is recommended for best results (use only a wide fan tip on single-ply membranes - do not allow stream to tear into roof surface). After cleaning, a roof must be allowed to thoroughly dry prior to application.

Allow to cure 4 - 8 hours before application of APOC[®] 545 SEBS roof coating. Up to 30 days may be required prior to application of Acrylic coatings. Do not apply under sheet of membranes. Do not heat or thin. DO NOT APPLY IF RAIN IS EXPECTED WITHIN 4 HOURS.

APPLICATION: For exterior use only. This product contains strong solvents and should only be used in a well ventilated are. Ensure protective clothing, gloves, and eyewear are worn during application of this product. For specific questions see SDS Sheet.

FOR BEST RESULTS: Apply on a clear, warm sunny day. Apply in morning hours to allow maximum cure time. Temperatures should be above 40 °F for proper trowelability, but not above 110 °F. APOC® 505 should be applied in a three course application using APOC® polyester reinforcement. APOC® 505 may be applied using a trowel, brush or putty knife. Keep container closed when not in use.

COVERAGE RATES: Product should be applied at the rate of 12 1/2 sq ft per gallon when applied 1/8" thick. For best results, apply in a 3 course fashion using APOC polyester reinforcement.

SUNLIGHT: Reflection of sunlight from light colored or white roof coatings necessitates the use of dark glasses to protect the eyes from glare during application and skin protection and/or sun block.

GENERAL INFORMATION: Storage of material shall be provided in cool, shaded areas during hot weather and as close as possible to room temperatures during cold weather.

CLEAN-UP: Paint thinner and mineral spirits.

©2008 Gardner-Gibson, Inc. Manufactured by / Fabricado por: Gardner-Gibson, Inc. P.O. Box 5449, Tampa, FL 33675

See SDS for more info

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

| Weight Per Gallon (ASTM D1475) | 8.65 lbs. |
|------------------------------------------|-----------------------------------|
| Solids by Weight (ASTM D2698) | 50.8% |
| Solids by Volume (ASTM D2697) | 40.1% |
| Elongation (ASTM D2370) | 209% |
| Tensile Strength (ASTM D2370) | 556psi |
| Reflectivity (ASTM C284) | 88.0 |
| Permeability (ASTM D1653) | <4 |
| Tool Application | Brush/Trowel |
| Skin Time (50% Relative Humidity, 70 °F) | 15 minutes |
| Full Cure (50% Relative Humidity, 70 °F) | 24 - 48 hours |
| Application Temperatures | 40 °F - 110 °F |
| Flammability | 80 °F |
| Clean-up Tools | Paint thinner and mineral spirits |

Approx. Shipping Weights: (Note: All approx. weights include container)

1 gallon (3.8L) 10.7 lbs. 3 gallon (11.36L) 32 lbs.

VOC: <300 g/L (regulatory)

HANDLING PRECAUTIONS: Product safety information required for safe use is not included. Before handling, read product safety data sheets and container labels for safe use and for physical and health hazard information. Safety Data Sheets are available on the APOC website at www.apoc.com. You can also obtain a copy from your local APOC Distributor or APOC sales representative.

LIMITED WARRANTY AND DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact APOC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with APOC warranty procedures and program.

For limited warranty and disclaimer information, visit our website at: www.apoc.com/productwarrantyinfo.

