



DESCRIPTION: APOC® 601 Eterna-Dri™ waterproofing is a liquid applied, gel based coating designed for use in the construction of homes and buildings. Eterna-Dri™ seals and protects foundations, basements and exterior walls and is designed to stop water intrusion, air seepage and vapor transmission. It is ideal to use on masonry, cinderblock, concrete block, stucco, brick and other approved substrates. This product dries to a blue-green color that can be painted.

PREPARATION: Clean or power wash surfaces to be coated. Salt deposits (efflorescence), peeling or blistered paint, dirt, dust, chalk, grease, and form release agents must be removed prior to application. Remove all rust or loose paint from metal surfaces. Patch cracks and seams with APOC® 601 Eterna-Dri™, and feather for a smooth surface. Reinforce with APOC 483 polyester over all cracks 1/16" wide or grater. Do not apply over damp or wet surfaces. Apply only after concrete and masonry has cured and is dry. Perform peel adhesion test to insure good adhesion.

APPLICATION: Formulated to be used when air and surface temperatures are above 10 °C (50 °F) and rising. Stir thoroughly prior to and during use. Apply with a heavy nap paint roller directly to walls to be waterproofed. A professional airless sprayer can also be used. If sprayed back roll 1st coat to insure adhesion. A minimum of two full coats are required for proper protection. Apply second coat perpendicular to the first coat.

DRY TIME: Allow a minimum 1 - 2 hour dry time between coats.

COVERAGE RATE: This pail will cover a total surface area of 100 sq. ft. or 9.29 m² in a 2 coat application. Each coat of APOC® 601 Eterna-Dri™ must be applied to a wet film thickness of 40 mills (2.5 gallons per 100 sq. ft.) or 1.02 mm (2.5 gallons per 9.29 m²) and should not exceed 50 wet mil thickness or 1.27 mm during each coat. Two coats MUST be applied in all applications. Final dry mil thickness after 2 coats must be a minimum of 30 Dry Mills or 0.77 mm.

CLEAN-UP: Tools should be cleaned with soap and water.

©2016 Gardner-Gibson, Inc.
Manufactured by / Fabricado por:
Gardner-Gibson, Inc.
P.O. Box 5449, Tampa, FL 33675

See SDS for more info

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	10.19 lbs.
Residue by Evaporation	37.50%
Combustible Solvents	0%
Hydrostatic Pressure Resistance (ASTM C 1306)	Pass
Water Vapor Transmission (ASTM E 96(A))	0.06 Perms
Peel Adhesion (in water) (ASTM C 794 / C 957)	Pass
Consistency	120 - 130 KU
Cure Time (at recommended coverage)	3 hours - Dry to Touch/ 72 hours - Full Cure
Application Temperatures Above	32 °F
Flammability (Flash point, °F solvent)	245 °F
Clean-up Tools	Soap & Water

Approx. Shipping Weights: (Note: All approx. weights include container)

18.9 L	50.95 lbs.
--------	------------

VOC: <50 g/L (regulatory)

HANDLING PRECAUTIONS: Product safety information required for safe use is not included. Before handling, read product safety data sheets and container labels for safe use and for physical and health hazard information. Safety data sheets are available on the APOC website at www.apoc.com. You can also obtain a copy from your local APOC Distributor or APOC sales representative.

LIMITED WARRANTY AND DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact APOC to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. Liability, if any, is limited to replacement of product unless installed by an approved contractor in accordance with APOC warranty procedures and program.

For limited warranty and disclaimer information, visit our website at: www.apoc.com/productwarrantyinfo.