



ARDEX TECHNICAL UPDATE

Update 50

December 12, 2014

To: ARDEX Sales Professionals, Sales Managers, Corporate (select), LevelMaster Elite Installers, Choice Contractors

From: ARDEX Technical Department

Extending ARDEX ERM with Aggregate

We are writing to confirm our recommendations for extending ARDEX ERM with aggregate.

The recommendation is as follows: For individual lifts of ARDEX ERM that will be thicker than 2", including full-depth repairs, extend each bag of ARDEX ERM with 25 pounds of clean, uniformly graded, 1/4" to 3/8" pea gravel dampened to an SSD condition.

The ARDEX ERM technical brochure is currently in the process of being updated.

Please note that the ARDEX ERM recommendation aligns with the other ECRS structural repair mortar recommendations, which call for the addition of 25 pounds of aggregate for thicker applications.

Should you have any questions on this information, or if we can be of further assistance, please contact the ARDEX Technical Service Department.

A handwritten signature in black ink, appearing to read "Seth Pevarnik".

Seth Pevarnik
Director of Technical Services

ARDEX AMERICAS 400 ARDEX Park Drive Aliquippa PA 15001

P: 724-203-5000 F: 724-203-5001 www.ardexamericas.com