

ARDEX PC-T™

Polished Concrete Topping

Self-leveling topping base for floors that will receive a polished concrete surface. Designed for use with ARDEX Polished Concrete Systems.

Install over: the surface of existing concrete to produce a new wear layer

Key Features


- Self-drying
- Portland cement-based
- Interior use
- Pourable and pumpable
- Available in light gray, gray, and white

Installation

- **General priming recommendations:** EP 2000™ Substrate Preparation Epoxy Primer with sand broadcast; See the ARDEX EP 2000™ technical brochure
- **Packaging:** 50 lb (23 kg)
- **Coverage:** 16.7 sq. ft. per bag at 3/8" (1.6 m² at 9.5 mm)
- **Thickness:**
 - Neat: 3/8" to 2" (9 mm to 5 cm)
 - Aggregate: up to 5" (13 cm)
- **Flow time:** 10 minutes
- **Walkable:** 2 to 3 hours
- **Polish:** 24 to 72 hours

Performance

- **ASTM C191 Initial Set:** Approx. 10 minutes
- **ASTM C191 Final Set:** Approx. 45 minutes
- **ASTM 109 mod (air cure only) Compressive Strength:** 6100 psi (427 kg/cm²) at 28 days
- **ASTM C348 Flexural Strength:** 1200 psi (84 kg/cm²) at 28 days
- **VOC:** 0



POLISHED CONCRETE SYSTEMS



AMERICAS

888-512-7339

+1-724-203-5000

www.ardexamericas.com

AF357 01/16