# ARDEX SD-P® RAPID

## Self-Drying, Trowelable **Concrete Underlayment**

Fast setting patch for smoothing and repairing concrete floors, ramps and stairways, as well as non-porous substrates such as terrazzo, ceramic and quarry tile, prior to the installation of floor covering.

## **Key Features**

- Formulated with a special blend of Portland cement, and other hydraulic cements and polymers
- Ideal for ramping, patching large areas and screeding
- Rapid setting
- Fluid consistency for ease of application
- Mixes with water only no latex additive necessary
- Exceptional bond strength

### Installation

- General priming recommendations:
  - No priming is required over standard absorbent concrete.
  - Over non-porous substrates, use ARDEX P 82™ Ultra Prime.
- Packaging: 40-lb. bag (18 kg)
- Coverage: 25 ft<sup>2</sup> per bag at 1/4" (2.3 m<sup>2</sup> at 6 mm) 50 ft<sup>2</sup> per bag at 1/8" (4.6 m<sup>2</sup> at 3 mm)

Coverage will vary depending on the texture of the surface being smoothed.

- Thickness:
  - Install neat up to 1" (25.4 mm)
  - Up to 3" (7.6 cm) with aggregate
- Install:
  - Most floor covering in as little as 60 minutes
  - Wood flooring or high-performance adhesives, such as epoxies or urethanes after 16 hours

#### **Performance**

- ASTM C191
  - Initial Set: Approx. 30 minutes
  - Final Set: Approx. 60 minutes
- ASTM C109/mod Compressive Strength (Air cure only) -4,200 psi (294.0 kg/cm<sup>2</sup>) at 28 days
- ASTM C348 Flexural Strength -1,000 psi (70.0 kg/cm<sup>2</sup>) at 28 days
- **VOC**: 0

FOR PROFESSIONAL USE ONLY.




Visit www.youtube.com/ARDEX101 to watch ARDEX Americas product videos.

For easy-to-use ARDEX Product Calculators and Product Information On the Go, download the ARDEX App at the iTunes Store or Google Play.













Refer to the technical data sheet at www.ardexamericas.com or call. 888-512-7339 prior to installation. For free ARDEX product training, click on ARDEX Academy. © 2016 ARDEX Engineered Cements, L.P. All rights reserved.

