

Color vs. Material Reference Guide

Color Description, Name		Ref. #	Steel Gauge			Aluminum Gauge				Initial Solar Reflectance	Thermal Emittance	Solar Reflectance Index (SRI)	Light Reflectance Value
Standard Colors			29	24	22	0.032	0.040	0.050	0.063				
Classic Bronze		1	*	*	*	*	*	*	*	0.12	0.82	4	4.09
Black		2	*	*	*	*	*	*	*	0.05	0.86	-2	5
Medium Bronze		3	*	*	*	*	*	*	*	0.33	0.86	34	11
Chocolate Brown		4	*	*	*	*	*	*	*	0.26	0.86	24	7
Concord Cream		5	*	*	*	*	*	*	*	0.65	0.85	78	62.13
Sandstone		6	*	*	*	*	*	*	*	0.57	0.85	66	49.76
Redwood		7	*	*	*	*	*	*	*	0.24	0.84	22	5.54
Mission Red		8	*	*	*	*	*	*	*	0.41	0.86	45	15
Sierra Tan		9	*	*	*	*	*	*	*	0.48	0.86	54	32
Ascot White		10	*	*	*	*	*	*	*	0.64	0.86	83	68
Forest Green		11	*	*	*	*	*	*	*	0.28	0.85	27	10
Patina Green		12	*	*	*	*	*	*	*	0.46	0.86	51	24
Dove Grey		13	*	*	*	*	*	*	*	0.5	0.83	55	35.18
Siam Blue		14	*	*	*	*	*	*	*	0.34	0.85	35	18.94
Rawhide		15	*	*	*	*	*	*	*	0.55	0.85	64	40.02
Rocky Grey		16	*	*	*	*	*	*	*	0.29	0.86	28	14
Regal Blue		18	*	*	*	*	*	*	*	0.27	0.86	26	10
Teal		19	*	*	*	*	*	*	*	0.3	0.85	30	10.56
Slate Grey		20	*	*	*	*	*	*	*	0.4	0.83	42	17.13
Slate Blue		21	*	*	*	*	*	*	*	0.31	0.86	31	18.32
Boysenberry		25	*	*	*	*	*	*	*	0.28	0.86	28	8
Bone White		26	*	*	*	*	*	*	*	0.74	0.86	90	76
Hartford Green		27	*	*	*	*	*	*	*	0.25	0.85	23	5.03
Hemlock Green		30	*	*	*	*	*	*	*	0.3	0.86	30	17.18
Charcoal Grey		62	*	*	*	*	*	*	*	0.29	0.82	27	10.01
55% Al-Zn Alloy Coated Steel with Acrylic Coating		97	*	*	*	*	*	*	*	0.68	0.14	58	
Mill Finish-Aluminum		99	*	*	*	*	*	*	*	-	-	-	-
Matte Finish			29	24	22	0.032	0.040	0.050	0.063				
Char Brown		29	*	*	*	*	*	*	*	0.24	0.84	20	4.34
Matte Black		32	*	*	*	*	*	*	*	0.09	0.84	2	3.7
Ash Grey		33	*	*	*	*	*	*	*	0.5	0.86	57	37
Thunder Grey		34	*	*	*	*	*	*	*	0.26	0.86	25	13
Almond		36	*	*	*	*	*	*	*	0.64	0.86	76	60
Anchor Grey		37	*	*	*	*	*	*	*	0.39	0.84	41	17.77
Premium Finish			29	24	22	0.032	0.040	0.050	0.063				
Brite Red		17	*	*	*	*	*	*	*	0.41	0.83	43	8.22
Coppertone		23	*	*	*	*	*	*	*	0.52	0.83	58	24.54
Antique Patina		24	*	*	*	*	*	*	*	0.26	0.85	24	14.33
Silversmith		28	*	*	*	*	*	*	*	0.54	0.82	60	31.03
Champagne		31	*	*	*	*	*	*	*	0.59	0.82	67	38.46
Titanium		35	*	*	*	*	*	*	*	0.59	0.84	68	38.63
Clear Satin Anodized		70	*	*	*	*	*	*	*	0.77	0.7	92	
Dark Bronze Anodized		71	*	*	*	*	*	*	*	0.15	0.77	6	
Woodland Series			29	24	22	0.032	0.040	0.050	0.063				
Driftwood		53	*	*	*	*	*	*	*				
Cedar		54	*	*	*	*	*	*	*				
Walnut		55	*	*	*	*	*	*	*				
Birch		57	*	*	*	*	*	*	*				
Oxide Series			29	24	22	0.032	0.040	0.050	0.063				
Copper Brown		42	*	*	*	*	*	*	*				
Tarnished Red		47	*	*	*	*	*	*	*				
Advanta Americana Classic (stamped shingles)			29	24	22	0.032	0.04	0.05	0.063				
Asheland Slate		AS	*	*	*	*	*	*	*	0.44	0.83	48	
Baja Slate		BS	*	*	*	*	*	*	*	0.27	0.83	25	
Beech Tree		BT	*	*	*	*	*	*	*	0.38	0.84	40	
Deep Granite		DG	*	*	*	*	*	*	*	0.25	0.83	22	
Quarry Slate		QS	*	*	*	*	*	*	*	0.31	0.84	31	
Rocky Cliff		RC	*	*	*	*	*	*	*	0.29	0.83	27	
Shaded Spruce		SS	*	*	*	*	*	*	*	0.25	0.83	22	
Weathered Stone		WN	*	*	*	*	*	*	*	0.27	0.83	25	
Willow Slate		WS	*	*	*	*	*	*	*	0.3	0.83	29	