

LAMINATED CRAWLSPACE INSULATION

CRAWLSPACE WALL APPLICATIONS

Insulation is a vital component of a building's envelope. For building designers requiring the highest quality rigid insulation, ThermalStar® Laminated Crawlspace Insulation (LCI) provides unmatched quality, with a stable long term R-value that will last the lifetime of your structure.

Manufactured under an industry leading quality control program monitored by UL and ICC-ES, ThermalStar LCI meets or exceeds ASTM C578 standards, providing an HFC free, recyclable rigid insulation with a low Global Warming Potential (GWP).

PHYSICAL PROPERTIES

PROPERTY	ASTM TEST METHOD	LCI		LCI GPS	
		10	15	10	15
Compressive Strength (psi) at 10% Deformation ¹	D1621	10	15	10	15
ASTM Classification	C578	Type I	Type VIII	Type I	Type VIII
R-value per inch at 75°F Mean Temperature	C518	3.9	3.9	4.7	4.7
R-value per inch at 40°F Mean Temperature	C518	4.2	4.3	4.9	4.9
R-value per inch at 25°F Mean Temperature	C518	4.4	4.5	5.1	5.1
Flexural Strength (psi)	C203	25	30	25	35
Water Absorption (% by volume) 24 Hour Immersion	C272	1.0	1.0	1.0	1.0
Water Vapor Permeance (perms)	E96	0.3	0.3	0.3	0.3
Surface Burning - Flame Spread	E84	<25	<25	<25	<25
Surface Burning - Smoke Developed	E84	<450	<450	<450	<450
Maximum Use Temperature	-	Short Term (10-15 minutes) 180°F, Long Term 165°F			

¹ ThermalStar LCI is elastic up to 1% deformation. A safety factor of 3 is recommended for long term loads to minimize long term deflection.

CODE COMPLIANCE

ThermalStar LCI complies with the model building codes when properly installed, as found in the following code reports and classification listings:

- ASTM C578 – (See product marking for type)
- Physical Properties – UL QORW.R16529
- Surface Burning – UL BRYX.R16529
- CAN/ULC-S102.2, S701 – ULC BOZCC.R16529
- International Energy Conservation Code (IECC) – ICC-ES ESR-1962, UL ER16529-01
- International Residential Code (IRC) – ICC-ES ESR-1962, UL ER16529-01
- International Building Code (IBC) – ICC-ES ESR-1962, UL ER16529-01

WARRANTY

ThermalStar LCI is backed by a limited lifetime warranty for physical and thermal performance, in addition to termite resistance. See separate ThermalStar warranty for terms and conditions.

STANDARD PRODUCT OFFERINGS

COMPRESSIVE STRENGTH	10 psi, 15 psi
SIZE	4'x8' sheets
LCI THICKNESS	1-3/16", 2-3/8"
LCI GPS THICKNESS	1-1/16", 1-19/32", 2-1/8"

FOR ADDITIONAL RESOURCES, VISIT THE WALL INSULATION SECTION OF OUR WEBSITE [ATLASMOLDEDPRODUCTS.COM](https://www.atlasmoldedproducts.com)

GREATER COVERAGE
GREATER AVAILABILITY



Atlas Molded Products, a Division of Atlas Roofing Corporation

