

- **DESCRIPTION:** Closed-cell polyisocyanurate (polyiso) foam core integrally bonded to non-asphaltic, fiber-reinforced organic felt facers. ACFoam[®]-II is offered in a variety of thicknesses, providing long-term thermal resistance (LTTR) values from 5.7 to 26.8. Available in 4ft x 8ft (1220mm x 2440mm) and 4ft x 4ft (1220mm x 1220mm) panels. Manufactured in accordance with **ASTM C1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi) and CAN/ULC-S704 Type 2, Class 3 or Type 3, Class 3.**
- **ADVANTAGES:** ACFoam[®]-II is manufactured using CFC-free, HCFC-free, and HFC-free foam blowing technology with zero ozone depletion potential (ODP) and virtually no (negligible) global warming potential (GWP). ACFoam[®]-II contains between 52.9% and 27.6% recycled materials by weight *(Atlas Technical Bulletin: TB-2).*
- APPLICATION: Manufactured and tested for use in new and re-roofing applications. ACFoam[®]-II roof insulation shall be installed over the roof deck. ACFoam[®]-II is used in built-up (BUR), modified bitumen, metal, ballasted single-ply, mechanically attached single-ply and adhered single-ply roofing systems. These roofing systems depend on proper installation for successful performance. Refer to FM Approvals[®] RoofNav and UL Online Certifications Directory for additional application details.
- **INSTALLATION:** ACFoam[®]-II shall be kept dry before, during and after installation. This product will burn if exposed to an ignition source of sufficient heat and intensity. Do not apply flame directly to ACFoam[®]-II insulation. Refer to product packaging and *PIMA Technical Bulletin #109* for storage and handling recommendations. **An offset or staggered multi-layer application of ACFoam[®] is strongly recommended when the total insulation thickness exceeds 2.7"** (*Atlas Technical Bulletin: TB-5).* Typical field fastening requirements can be obtained from membrane system manufacturer or FM Global Property Loss Prevention Data Sheets 1-29.

Prior to installation, Atlas Roofing Corporation recommends that you consult your local building codes, contract documents, professional engineer, FM Global, Miami-Dade County and membrane manufacturer for additional installation guidelines as well as design enhancements.

ACFOAM-II MEETS OR EXCEEDS THE FOLLOWING PHYSICAL PROPORTIES

PROPERTY	TEST METHOD	ASTM C1289 OR CAN/ULC S704 Minimum requirements	
DIMENSIONAL STABILITY	ASTM D2126	< 2%	
COMPRESSIVE STRENGTH	ASTM D1621	20 psi (140 kPa) or 25 psi (172 kPa)	
WATER ABSORPTION	ASTM C209 & D2842	< 1.5%, < 3.5%	
WATER VAPOR TRANSMISSION	ASTM E96	< 1.5 perm (85.5ng/(Pa•s•m²))	
PRODUCT DENSITY	ASTM D1622	Nominal 2.0 pcf (32.04 kg/m³)	
FLAME SPREAD	ASTM E84 (10 min.)	¹ 40-60	
SMOKE DEVELOPMENT	ASTM E84 (10 min.)	¹ 50-170	
TENSILE STRENGTH	ASTM D1623	> 730 psf (35 kPa)	
SERVICE TEMPERATURE	-	-100°F to +250°F	

¹Numerical ratings are not intended to reflect performance under actual fire conditions. Flame spread index of \leq 75 and smoke development \leq 450 meet code requirements for foam plastic roof insulation. Codes exempt foam plastic insulation when used in FM 4450 or UL 1256. Physical properties listed above are presented as typical average values as determined by accepted ASTM test methods and are subject to normal manufacturing variation.

- ASTM C1289, Type II, Class 1, Grade 2 (20 psi) or Grade 3 (25 psi)
- CAN/ULC-S704, Type 2, Class 3 or Type 3, Class 3
- CCMC No. 12464-L
- UL Certified for Canada Insulated Roof Deck Assemblies Construction No. C38 and 52. Meet CAN/ULC-S126, CAN/ULC-S101 and CAN/ULC-S107
- UL Standard 1256 Classification Construction No. 120, 123 & 292
- UL Standard 790 (ASTM E108) Roofing Systems Classification
- UL Standard 263 (ASTM E119) Fire Resistance Classification

THERMAL DATA

² LTTR VALUE	THICKNESS		³ RSI	FLUTE SPANABILITY	
	in	mm	°K9I	in	mm
5.7	1.0	25.4	1.00	2.625	66.68
8.6	1.5	38.1	1.50	4.375	111.13
11.4	2.0	50.8	2.01	4.375	111.13
14.4	2.5	63.5	2.53	4.375	111.13
17.4	*3.0	76.2	3.06	4.375	111.13
20.5	*3.5	88.9	3.60	4.375	111.13
23.6	*4.0	101.6	4.15	4.375	111.13

²LTTR (long term thermal resistance) values were determined in accordance with CAN/ULC-S770-09. Test samples were third-party selected and tested by an accredited material testing laboratory. The LTTR results were reviewed by FM Global and certified by the PIMA Quality Mark Program. ³RSI is the metric expression of R-value (m² • K/W). * To minimize the effects of thermal bridging, Atlas strongly recommends the use of multiple layers when the total desired or specified R-value requires an insulation thickness greater than 2.7° thick.

- UL Standard 1897 Uplift Resistance
- FM Standard 4450/4470 Approved Refer to FM Approvals[®] RoofNav for Specific System Details
- IBC Chapter 26 & NBC Sections on Foam Insulation
- California State Insulation Quality Standards and Title 25 Foam Flammability Criteria (License #T 1231)
- Miami-Dade County Approved
- State of Florida Product Approval (FL17989)
- Has acheived GREENGUARD GOLD Certification

Other than the aforementioned representations and descriptions, Atlas Roofing Corporation (hereafter, "Seller") makes no other representations or warranties as to the insulation sold herein. The Seller disclaims all other warranties, express or implied, including the warranty of merchantability and the warranty of fitness for a particular purpose. Seller does, however, have a limited warranty as to the LTTR-Value of the insulation, the terms of which are available upon request from the Seller. Seller shall not be liable for any incidental or consequential damages including but not limited to the cost of installation, removal, repair or replacement of this product. Buyer's remedies shall be limited exclusively to, at Seller's option, the repayment of the purchase price or resupply of product manufactured by Atlas in a quantity equal to that of the nonconforming product. Atlas distributors, agents, salespersons or other independent representatives have no authority to waive or alter the above limitation of liability and remedies.



PRODUCT CERTIFIED FOR LOW CHEMICAL EMISSIONS: UL.COM