



Technical Data Sheet PVC Waterstop Compound

<u>Typical Properties (0.075" Slab)</u>	<u>Nominal Value</u>	<u>ASTM Method</u>
Water Absorption	0.15%	D-570
Tear Resistance	350/lb.in.	D-624
Specific Gravity, (+/-0.02)	1.33	D-792
Hardness, Shore A (+/-3, 10 sec. Delay)	74	D-2240
Tensile, psi	2075	D-638, Type IV
Elongation, %	435	D-638, Type IV
100% Modulus, psi	725	D-638, Type IV
Brittle Point (Tb), °F	-37 (Passed)	D-746
Stiffness in Flexure, psi	1440	D-747
Ozone Resistance	No Failure	D-1149
<u>Accelerated Extraction, CRD-C572</u>		
Tensile, psi	2025	D-638, Type IV
Elongation, %	420	D-638, Type IV
<u>Effect of Alkali, CRD-C572</u>		
Weight Change, %	+0.05	_____
Change in Hardness, Shore A	-3	D-2240

This material meets or exceeds U.S. Army Corps of Engineers specification **CRD-C572-74**.

141 Hammond Drive • Carrollton, Georgia 3017 • 770.832.2000 • 800.862835 • FAX 770.832.2095
Visit our website @ www.bometals.com • Address email to info@bometals.com

IMPORTANT: The technical data herein is believed to be accurate. It is offered for your consideration, investigation and verification. Buyer assumes all risk of use, storage and handling of the product. NO WARRANTY, EXPRESS OR IMPLIED, IS MADE INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Nothing contained herein shall be construed as a license to operate under or recommendation to infringe any patents.