



915FS

FAST SETTING POLYURETHANE SEALANT & ADHESIVE

KEY FEATURES

- Accelerated skin time
- Tenacious bond to difficult substrates
- Permanently flexible

DESCRIPTION

Bostik 915FS is a one-component, smooth fast setting polyurethane sealant/adhesive capable of dynamic joint movement totaling 70% of original joint geometry ($\pm 35\%$). The sealant cures to a tough, flexible rubber when exposed to moisture present in the atmosphere.

Bostik 915FS has physical properties that will remain relatively stable over time and in varying weather conditions. Its physical properties are relatively unchanged over a wide temperature range, -40°F to 150°F (-40°C to 66°C). Where textured appearance is needed, please use Bostik 916 or Bostik 2000 Textured.

APPLICABLE STANDARDS

- ASTM C920, TYPE S, GRADE NS, CLASS 35 USE NT, A AND M.
- US Federal Specification TT-S 00230C (COMB-NBS) for one-component sealants as Class A, non-sag.
- CARB, SCAQMD, and OTC compliant.
- Canadian Specification CAN/CGSB 19.13-M87.

BASIC USES

Bostik 915FS is designed for sealing expansion and control joints, for use under deck coatings, for sealing various roofing and siding applications, such as metal roofs, gutters, roof tile applications, and for sealing perimeters of doors, windows, and other wall penetrations.

Bostik 915FS cures to form a durable, flexible bond with most building materials in any combination including stone, masonry, ceramic, wood, steel, aluminum, copper, bondarized and Kynar coated metals, and many other synthetic materials.

INSTALLATION PROTOCOL

Joint Design: In general, more joint movement can be accommodated in a thin bead of sealant than a thick bead. Bostik 915FS should be no thicker than $1/2"$ (12.7mm) and no thinner than $1/4"$ (6.4mm). In joints between $1/2"$ and $1"$, the ratio of sealant width to depth should be approximately 2:1. Sealant



depth in joints between $1/4"$ and $1/2"$ should be $1/4"$ deep. Joints with dynamic movement should not be designed in widths less than $1/4"$.

Surface Preparation: See limitations about surface preparation. Surfaces must be structurally clean, dry (no frost) and structurally sound, free of contaminants, including, but not limited to, dust, dirt, loose particles, tar, asphalt, rust, mill oil, etc. If substrate is painted or coated, scrape away all loose and weakly bonded paint or coating. Any paint or coating that cannot be removed must be tested to verify adhesion of the sealant or to determine the appropriate surface preparation if needed. (See ASP section on next page for details.)

To remove laitance and any other loose material, clean concrete, stone or other masonry materials with non-alcoholic based solvent by washing, grinding, sandblasting or wire brushing as necessary. Do not use water to clean substrates. Dust must be thoroughly removed after cleaning.

Alcohol is not compatible with polyurethanes and its use can cause irreparable damage to the sealant. If alcohol is used as a cleaning solvent, all traces of alcohol must thoroughly be removed prior to the installation of the polyurethane sealant. Lastly, alcohol is **NOT** recommended as a tooling medium.

Backer Rods and Bond Breaker Tapes: Bond breakers including, but not limited to, closed-cell polyethylene backer rods are used to control depth of the sealant bead, provide a firm tooling surface and avoid three-sided adhesion. Where the depth of joint

prevents use of backer rods, a polyethylene strip or tape must be used as a bond breaker to prevent 3-sided adhesion. Do not prime or damage the surface of the bond breaker. Refer to instructions given by rod and tape manufacturers for the correct backer rod and tape size related to joint size.

Priming: In general, application of Bostik 915FS does not require priming the substrates. However, some substrates may require a Bostik primer. It is the user's responsibility to check adhesion of the cured sealant on typical test joints at the project site before and also during application as weather conditions may affect the adhesion results (See ASP section on next page.). Refer to Bostik Primer product data sheet or call Technical Service (1-800-726-7845) for proper selection and application of Bostik Primers.

Tooling: Bostik 915FS comes ready-to-use. Cut spout or tip to desired bead size. Apply moderate pressure to break seal inside the nozzle. Apply by using a professional caulking gun. Use opened cartridges and sausages the same day they are opened. Apply Bostik 915FS in a continuous operation using positive pressure to the bottom of the joint to properly fill and seal the joint. When applying, avoid air entrapment and overlapping. Tool the sealant before the skin forms with adequate pressure to spread the sealant against the backup material at the bottom and sides of the joint. A dry tool with a concave profile is recommended for that operation. Do not use water or soapy water for this operation. Avoid smearing and feathering of the sealant to allow full performance of the cured seam. Excess sealant should be dry-wiped or joints should be properly taped.

Cleaning: After dry-wiping uncured sealant from substrates and tools, remaining uncured sealant can be removed by using Xylene, Toluene or similar aromatic solvents. Please refer to the MSDS provided for these solvents before use. Bostik Hand Towel and Specialty Sealant Remover can also remove uncured sealant. Cured sealant is usually very difficult to remove without altering or damaging the surface to which the sealant has been misapplied. Cured sealant can be removed by abrasion or other mechanical means (scrapers, putty knives).

Curing Time: Bostik 915FS is a moisture cure, polyurethane sealant. On wood, with ambient air at 50% relative humidity and at 73°F, Bostik 915FS will generally skin within one and a half hours. Lower temperature and lower relative humidity will significantly increase the skin time and cure time of a polyurethane sealant.

Painting and Coating: Bostik 915FS is not an RTV silicone and therefore is suitable for painting with latex-based paints. Paint chemistries and flexibility characteristics of the paint films over the sealant may affect wetting, adhesion and integrity of the paint layer, and it is therefore mandatory to pretest the paint or other coating over the Bostik 915FS™ to ensure the successful compatibility between the sealant and the paint/coating after a sufficient amount of time. See your paint manufacturer for specifications or limitations and call our Technical Service (1-800-726-7845) for more information. In general, oil-based paints are not recommended because of their poor elastic properties and because of their potential interaction with the sealant chemistry, which may create non-curing conditions for the painted sealant. Do not paint over the polyurethane sealant until it has fully cured.

Maintenance: If the sealant becomes damaged, replace the damaged portion by removing the old sealant completely, cleaning the surfaces and reapplying a fresh and appropriate amount of new sealant in accordance with the directions and information contained in this data sheet.

MANDATORY ADHESION TO SUBSTRATES

PRETEST— (ASP)

A hand pull test must be run before the job starts and at regular intervals during the job. It must be run on the job site after the sealant is fully cured, usually within 7 to 21 days. (Adhesion may develop fully after at least 14 days.) The hand pull test procedure is as follows:

1. Make a knife cut horizontally from one side of the joint to the other.
2. Make two vertical cuts approximately two inches long, at the sides of the joint, meeting the horizontal cut at the top of the two-inch cuts.
3. Grasp the two-inch piece of sealant firmly between the fingers and pull down at a 90° angle or more, and try to pull the uncut sealant out of the joint.
4. If adhesion is sufficient, the sealant should tear cohesively in itself.
5. Sealant may be replaced by applying more sealant in the same manner as it was originally applied. Care should be taken to ensure that the new sealant is in contact with the original, and that the original sealant surfaces are clean, so that a proper bond between the new and old sealant will be obtained.

PACKAGING

10.1 fl. oz. Cartridges, 24 Cartridges/Case

20 fl. oz. Sausages, 12 Sausages/Case

STORAGE, PACKAGING & SHELF LIFE

Shelf life of Bostik 915FS must be checked prior to using the product; do not use past its shelf life. Caulk past its shelf life may not perform or adhere as described by this data sheet. High temperature and high relative humidity may reduce significantly the shelf life of polyurethane sealants. If you are unsure of the expiration date of your Bostik product, please call customer service at 1-800-7/BOSTIK (1-800-726-7845) to check if the product is still within its shelf life.

COLORS

White	Stone	Bronze	Limestone
Black	Md. Bronze	Capitol Tan	Light Gray
Terra Cotta	Antique White		Aluminum Gray

AVAILABILITY

Available from authorized Bostik distributors. Go to www.bostik-us.com and check on our distributor locator for the closest distributor in your location or call customer service at 1-800-7/BOSTIK (1-800-726-7845).

WARNING

IRRITANT. MAY CAUSE ALLERGIC SKIN OR LUNG REACTION. MAY IRRITATE EYES, SKIN AND LUNGS. Contains a potential skin and lung sensitizer. May cause allergic respiratory tract or skin reaction, including dermatitis. Avoid breathing mists or vapors. Avoid contact with skin and eyes. Use in a well-ventilated area or wear a mask. Store in a cool 60° - 80°F (15° - 30°C), dry, well-ventilated area away from heat, ignition sources and direct sunlight.

KEEP OUT OF THE REACH OF CHILDREN

FIRST AID TREATMENT

Contains Phthalates, Methylene Diphenyl Isocyanate (MDI), Carbon Black or Titanium Dioxide inextricably bound in a


polymer matrix. If in eyes or on skin, rinse with water for at least 15 minutes. If on clothes, remove clothes. If breathed in, move person to fresh air. If swallowed, call a Poison Control Center or doctor immediately.

SEE SAFETY DATA SHEET.

APPLICATION LIMITATIONS

- Construction substrates have become complex and diverse by nature and origin. Substrate chemistries and structures can interfere with adhesive performances of the sealant. Adhesion to Substrate Pretest (ASP) is therefore MANDATORY to assess any adhesion and sealing characteristics—see Adhesion to Substrates Pretest (ASP) section and see Installation Protocol section. This must be done pre-installation to avoid potential failures. Call Technical Service (1-800-726-7845) for more information about surface preparation and possible priming.
- Do not apply over damp, contaminated, loose surfaces (See Installation Protocol and Surface Preparation), old sealants or other foreign substances that may impair the adhesion bond. Avoid air entrapment.
- Dampness and substrates with high moisture content will trigger extensive curing of the sealant within a very short period of time. This may cause an excess of bubbling and foaming within the sealant and at the bottom of the bead.
- High temperature/humidity can cause the sealant to develop bubbles during the curing process.
- Sealant installation is not recommended when the dew point of the substrate is close to ambient temperature or a moisture-vapor transmission condition is present increasing the potential for bubbling to form during cure.
- Porous substrates such as, but not limited to, marble, limestone, and granite might absorb components of the Bostik 915FS leading to staining of the substrate. **ASP with sufficient aging is mandatory to assess this potential issue.**
- The ultimate performance of Bostik 915FS depends on proper joint design and proper application with joint surfaces properly prepared (See Installation Protocol). Bostik 915FS is not recommended for joints with dimensions less than or greater than what is recommended below. (See Installation Protocol – Joint Design section.)
- Bostik 915FS must not be used to seal narrow joints, fillet joints and face nail holes.
- Smearing and feathering Bostik 915FS over joints is not recommended.
- Bostik 915FS is not recommended for horizontal joints or traffic-bearing joints where abrasion resistance is required (walkways, driveways, runways, etc.). Please refer to Bostik 955-SL, Bostik 555-SL or Bostik 505 for this application.
- Bostik 915FS™ is not recommended for continuous immersion in water or any other fluid. When fully cured, avoid exposure, even incidental, to fuels, chlorinated solvents, acid and alkaline solutions. Bostik 915FS is not recommended for exterior or interior sealing below the waterline; please refer to Bostik 940 Fast Set for marine applications.
- Contact of Bostik 915FS with asphalts (i.e., back coating of window flashing, etc.) and other filler compounds impregnated with oil, asphalt, tar, etc., may deteriorate the cohesive strength of the substrate and ultimately compromise the seal. Please refer to Bostik PRO-MS 50 for this application.
- During the curing of Bostik 915FS, do not expose to curing silicone sealants, curing Bostik 2000, Bostik PRO-MS 50, Bostik 2020,

MANDATORY ADHESION TO SUBSTRATE (ASP) FIELD TEST



alcohol, acids or solvent-based materials.

- Compatibility to copper-based substrates (i.e., flashing) can vary due to, but not limited to, age and joint size. Please consult Technical Service (1-800-726-7845) for details.
- Lower relative humidity and temperature will significantly extend the curing time. Confined areas, deep joints and moisture barrier substrates may also affect the full cure time and extend it by many days. Apply sealant in ambient air temperature of 40° F. and rising.
- Bostik 915FS may remain tacky for a few hours and attract dust and dirt from the jobsite which may affect the appearance of the sealant. Check tack-free time to prevent dirt pickup.
- Bostik 915FS is not recommended for glazing applications. Bond line strength can be affected by UV rays through the clear material (glass, acrylic glass, polycarbonate, etc.).
- Bostik 915FS is not an RTV silicone and therefore is suitable for painting with latex based paints. Paint chemistries and flexibility characteristics of the paint films over the sealant may affect wetting, adhesion and integrity of the paint layer; and it is therefore mandatory to pretest the paint or other coating over the Bostik 915FS to ensure the successful compatibility between the sealant and the paint/coating after a sufficient amount of time. See your paint manufacturer for specifications or limitations and call our Technical Service (1-800-726-7845) for more information. In general, oil-based paints are not recommended because of their poor elastic properties and because of their potential interaction with the sealant chemistry, which may create non-curing conditions for the sealant. Do not paint over the polyurethane sealant until it has fully cured.
- The surface of a Bostik 915FS seal when exposed to UV rays and sunlight will yellow and will not retain its gloss. This phenomenon can occur within a few weeks after exposure. The change of color is limited to the surface layer of the seal and should not compromise the sealing properties of the Bostik 915FS if the dimensions of the joint are proper and the sealant is otherwise properly applied. In areas where color retention is critical, please refer to Bostik 2000, Bostik 2020 and Bostik PRO-MS 50. Bostik 915FS may remain tacky for a few hours and attract dust and dirt from the jobsite which may affect the appearance of the sealant. Check tack-free time to prevent dirt pickup.

COVERAGE FOR 10.1 FL. OZ. (298 ML) CARTRIDGE

		Width							
Depth	1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"	
1/8"	99	49	33	24	20	16	14	12	
1/4"		24	20	12	10	8	7	6	
3/8"			11	8	6	5	5	4	
1/2"				6	5	4	3	3	

Linear Feet Per 10.1 fl. oz. Cartridge

COVERAGE FOR 20 FL. OZ. (600 ML) SAUSAGE

		Width							
Depth	1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"	
1/8"	288	145	95	71	58	48	40	36	
1/4"		71	58	36	29	23	20	17	
3/8"			32	23	17	16	13	11	
1/2"				17	14	11	10	8	

Linear Feet Per 20 fl. oz. Sausage

COVERAGE FOR 5 GALLON (18.9 L) PAIL

		Width							
Depth	1/8"	1/4"	3/8"	1/2"	5/8"	3/4"	7/8"	1"	
1/8"	6150	3100	2050	1540	1230	1025	870	770	
1/4"		1540	1240	770	615	510	440	370	
3/8"			680	510	410	310	290	245	
1/2"				370	305	245	220	185	

Linear Feet Per 5 Gallon Pail

LIMITED WARRANTY

Limited Warranty found at www.bostik-us.com or call 800.726.7845. TO THE MAXIMUM EXTENT ALLOWED BY LAW, BOSTIK DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. UNLESS OTHERWISE STATED IN THE LIMITED WARRANTY, THE SOLE REMEDY FOR BREACH OF WARRANTY IS REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW. DISCLAIMERS OF IMPLIED WARRANTIES MAY NOT BE APPLICABLE TO CERTAIN CLASSES OF BUYERS AND SOME STATES DO NOT ALLOW THE EXCLUSION OR LIMITATION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE ABOVE LIMITATIONS MAY NOT APPLY TO YOU. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. The Limited Warranty extends only to the original purchaser and is not transferable or assignable. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

PRIMER COVERAGE RECOMMENDATIONS

For one quart of primer, coverage is as follows

1 unit	5 gallon pail
5 units	1.5 gallon unit
7 gallons	1 gallon unit

*All values are approximations and can vary due to joint dimension variations, porosity, and texture of substrates. Yield per cartridge is approximate due to variables beyond Bostik's control, such as irregular joint configuration and installation technique.

TABLE 1: TYPICAL UNCURED PROPERTIES*

Property	Value	Test Method/Note
Tool/Work Time	70 min.	Bostik Test Method
Skin Time	90 min.	Bostik Test Method
Curing Time @77°F (25°C)	1.5-3 days	Varies w/relative humidity
Flow, Sag or Slump	0.3 inch	Bostik Test Method
Staining	None	ASTM C510

* Values given above are not intended to be used in specification preparation purposes.

TABLE 2: TYPICAL CURED PROPERTIES* (AFTER 14 DAYS CURE AT 77°F AND 50% RH)

Property	Value	Test Method/Note
Hardness (Shore A)	40-45	ASTM D2240
Tensile Strength @ Break	240 psi	ASTM D412
Adhesion Peel	>25 piw	TT-S-00230C / ASTM C 794
Ozone Resistance	Excellent	Bostik Method
UV Resistance	Good	Bostik Method
Temperature Resistance	-40° to 180°F	Bostik Method
Modulus @ 100% Elongation	65 psi	ASTM D 412
Elongation @ Break	850%	ASTM D 412
Stain and Color Change	None	ASTM C510
Joint Movement Capability	±35%	TT-S-00230C / ASTM C 719
Heat and Aging	Good	ASTM C1246
UV Resistance	Pass	ASTM C 793

* Values given above are not intended to be used in specification preparation purposes.



BOSTIK HOTLINE

Smart help
1-800-726-7845

Bostik, Inc.

11320 W. Watertown Plank Road
Wauwatosa, WI 53226

www.bostik.com/us

