

Tips on BRICKFORM® Cem-Coat™ Application

This is abbreviated information taken from the BRICKFORM Cem-Coat Technical Information Sheet and MSDS. Read both references before attempting to use this product. BRICKFORM strongly recommends testing an area for results before total application.

DO

PREPARATION

The application area must be totally free of any foreign materials.

MIXING

Use a power drill with a mixing attachment to mix the materials.
Scrape sides and bottom of container while mixing.

APPLICATION

Application temperatures should be between 50° and 80°.
The application surface should be damp.

CURING

Let the material cure for at least 24 hours after application.

SEALING

Use a high-quality sealer such as BRICKFORM Gem-Seal, high-gloss sealer, Master-Seal, slip-resistant sealer, or Satin-Seal, water-based, semi-gloss sealer.

MAINTENANCE

Inspect annually for signs of worn sealer and reapply as necessary.

DO NOT

PREPARATION

Do not leave any standing water after rinsing the concrete.

MIXING

Do not add liquid to powder.
Do not apply until all material is thoroughly mixed.

APPLICATION

Do not apply in direct sunlight or in inclement weather.
Do not apply over standing water.

CURING

Do not let the area get dirty or stained until it can be sealed.

SEALING

Do not use a penetrating sealer.
Do not seal unless CEM-COAT has cured for at least 24 hours.

MAINTENANCE

Do not reapply a sealer until all efflorescence and deleterious materials have been removed.

WARRANTY

This product is not intended for public use and is intended for use by licensed contractors and installers, experienced and trained in the use of these products. It is warranted to be of uniform quality, within manufacturing tolerances. The manufacturer has no control over the use of this product, therefore, no warranty, expressed or implied, is or can be made either as to the affects or results of such use. In any case, the manufacturer's obligations shall be limited to refunding the purchase price or replacing material proven to be defective. The end user shall be responsible for determining product's suitability and assumes all risks and liability.

SAFE HANDLING INSTRUCTIONS

DO NOT TAKE INTERNALLY. When working with or near this product, all personnel must wear OSHA-NIOSH approved respirators. Refer to OSHA standards in 29 CFR 1910.134. Avoid inhalation and use local exhaust to keep exposures below OSHA PEL's for silica and nuisance dusts. Avoid contact with skin and eyes. Wear rubber gloves and aprons to protect skin and wear safety eye goggles. Use good hygiene when handling this product and wash and bathe after each use. Be sure to wash clothing after each use.