

Concrete Curing Compounds

Carlisle is replacing literature references on Concrete Curing compounds with the following chart.

Product	Carlisle recommendation	Remedy if needed
CCW - 860	Vertical Walls - Strongly recommends no resin based compounds be used, no compound or self dissipating compound Horizontal - Very little affect	Wall may be hydro-blasted, aged, compound may be mechanical removed or adhesion tested Horizontal - test adhesion if desired
CCW-525	Water cure or use only 100% Sodium Silicate	Remove other compounds by mechanical means
Barricoat	Vertical Walls - Strongly recommends no resin based compounds be used, no compound or self dissipating compound Horizontal - Very little affect	Wall may be hydro-blasted, aged, compound may be mechanical removed or adhesion tested Horizontal - test adhesion if desired
CCW -500 /Vapor Loc	Vertical Walls - Strongly recommends no resin based compounds be used no compound or self dissipating compound Horizontal - Very little affect	Wall may be hydro-blasted, aged, compound may be mechanical removed or adhesion tested Horizontal - test adhesion if desired
CCW Clay	Any compound desired, will have no affect	No affect
Butyl	Vertical Walls - Strongly recommends no resin based compounds be used no compound or self dissipating compound Horizontal - Very little affect	Wall may be hydro-blasted, aged, compound may be mechanical removed or adhesion tested Horizontal - test adhesion if desired
EPDM	Vertical Walls - Strongly recommends no resin based compounds be used no compound or self dissipating compound Horizontal - Very little affect	Wall may be hydro-blasted, aged, compound may be mechanical removed or adhesion tested Horizontal - test adhesion if desired
Deck Coating	Water cure or use only 100% Sodium Silicate	Remove other compounds by mechanical means