# OEM INSULATION



AcoustaBlanket ™ Black is a black fiberglass blanket insulation with an abuse-resistant black surface used in commercial construction for acoustical control in theaters, studios and entertainment facilities. It has a black Class A surface for exposed applications.

#### **FEATURES & BENEFITS**

AcoustaBlanket $^{\text{m}}$  has a tough, durable, fire-resistant black nonwoven glass fabric top surface. This adds strength to the product during installation and use. The glass fibers resist bacteria and fungal growth, and will not rot or deteriorate.

#### **COMPOSITION & MATERIALS**

Composed of glass fibers firmly bonded together with a thermoset resin and overlaid with an extremely tough and durable abuse-resistant black composite facing with no printing on the top surface. The insulation is packaged in plastic bags to deliver a high volume of insulation.

### **APPLICATION**

Insulation should be kept dry at all times.

# **PACKAGE LABELING**

Individual rolls are wrapped in plastic film and labeled with product code and product information.

#### **INSTALLATION**

AcoustaBlanket $^{\mathbb{M}}$  Black insulation is applied to spandrel, pre-cast concrete panels with approved adhesives or mechanical fasteners. These installation recommendations are general in nature. Other methods may be acceptable. Please consult your contractor for recommendations best suited to the application.

#### **TECHNICAL DATA**

# APPLICABLE STANDARDS, CODE COMPLIANCE

Model Building Codes:

- ICC

#### **FIRE RESISTANCE**

Fire Hazard Classification:

– UL 723, ASTM E84, NFPA 255 Max. Flame Spread Index: 25 Max. Smoke Developed Index: 50

Limited Combustible:

- NFPA 259

< 3,500 btu/lb

Fire Safety Standards: - NFPA 90A, NFPA 90B

Acoustical Performance: See table on other side Thermal Performance: See table on other side

# PHYSICAL / CHEMICAL PROPERTIES

PROPERTY (UNIT)	TEST	VALUE			
Operating Limits: Temperature Air Velocity	ASTM C411 ASTM C1071	250°F / 121°C 6,000 fpm (30.5 m/s)			
Water Vapor Sorption:	ASTM C1104	≤ 3%			
Odor Emission:	ASTM C1304	Pass			
Corrosion Resistance:	ASTM C665	Pass			
Fungi Resistance:	ASTM C1338 ASTM G21	No growth			



#### **AVAILABLE SIZES**

Available standard sizes and Thermal Performance are listed in the table. Contact CertainTeed for availability and minimum order quantities.

TYPE	DENSITY	THICKNESS		WIDTH		LENGTH		R-VALUES	
		IN	ММ	IN	мм	FT	М	R	RSI
	1.5 pcf (24 kg/m³)	1	25	48	1219	100	30.5	4.2	0.74
150		11/2	38	48	1219	50	15.2	6.3	1.11
	2	51	48	1219	50	15.2	8.3	1.46	

ACOUSTICAL PERFORMANCE									
ABSORPTION COEFFICIENTS  © OCTAVE BAND CENTER FREQUENCIES (HZ)									
ТҮРЕ	THICKNESS		125	250	500	1000	2000	4000	NRC
	IN	ММ	123	250	300	1000	2000	4000	
	1	25	0.18	0.36	0.59	0.86	0.95	0.90	0.70
150	1½	38	0.35	0.51	0.83	0.93	0.97	0.96	0.80
	2	51	0.24	0.79	1.09	1.05	1.02	1.01	1.00

Sound absorption tested in accordance with ASTM C423 using Type A mounting per ASTM E795.

## **WARRANTY**

Refer to CertainTeed's Limited Warranty (30-32-113).

#### **MAINTENANCE**

No maintenance required.

#### **AVAILABILITY AND COST**

Sold throughout the United States, Canada, and Mexico. For availability and cost contact your local distributor or call CertainTeed Sales Support Group at 800-233-8990.

## **TECHNICAL SERVICES**

Technical assistance can be obtained either from your local CertainTeed sales representative, or by calling CertainTeed Sales Support Group at 800-233-8990.







