



## LEVELLINE®

### DRYWALL CORNER STICKS

CertainTeed LEVELLINE Outside 90 Drywall Corner Sticks are easy to install corners that deliver perfect corners in record time.

#### Features & Benefits

- Provides superior impact resistance, easier to repair damage.
- Joint tape on the interior creates a 100% bond to drywall.
- Less compound – Less dry time.\*
- Lighter and easier to cut than metal bead, no sharp edges or burring.
- Reduces storage and handling damage.
- Meets Class A Flame Spread and Smoke Developed Rating per ASTM E84 and CAN/ULC-S102.
- GREENGUARD Gold certified.

\* Based on contractor testimonials and internal testing.

#### Working with the Product

##### SITE CONDITIONS

The room temperature and wallboard should be maintained at 55°F (13°C) for 48 hours prior to application and continuously thereafter until compound is completely dry. Gypsum wallboard should be dry for at least 48 hours before the application of joint compounds. Continuous ventilation must be provided to ensure proper drying.

##### APPLICATION

Using the taping knife, apply joint compound to drywall, slightly beyond where the edge of the corner will be. Or use hopper to fill bead. Place corner trim on wall, ensuring it is aligned tightly to the ceiling. Press into position. Use the roller to embed the trim. Or embed using even pressure, running the knife over it at a 45° angle. Use the taping knife to skim over the edge with joint compound. Let dry thoroughly. Use the wider finishing knife to skim over the edge again. Let dry thoroughly. Lightly sand and paint.

#### PRODUCT DATA

PROPERTIES	LEVELLINE OUTSIDE 90
Lengths	6'10", 8', 9', 10', 12' (2083 mm, 2438 mm, 2743 mm, 3048 mm, 3658 mm)
Copolymer Edge and Center Thickness	≈ .035" (0.9 mm)
Total Flange Width	1-3/4" (44.45 mm)
Copolymer Flange Width	1-1/16" (27.0 mm)
Paperboard Edge Flap	5/8" (15.875 mm)
Packaging	50 Sticks/Carton

All products are available in custom lengths. Please contact your CertainTeed representative for more information.

#### TECHNICAL DATA

APPLICABLE STANDARDS AND REFERENCE	
Product Standard	ASTM C1047
Installation Guidelines	ASTM C840 / GA-216
Finishing Guidelines	ASTM C840 / GA-214 GA-216 / ASTM C475
Flame Spread / Smoke Developed Rating	Class A ASTM E84 / CAN/ULC-S102

Job Name \_\_\_\_\_

Contractor \_\_\_\_\_

Date \_\_\_\_\_

Products Specified \_\_\_\_\_

## CERTAINTEED ROLLERS

Apply corners quickly and easily with an CertainTeed Outside 90 roller. Just place corner trim on the wall and use the roller to press it into place for a perfect fit.

## BOX IT

Box up to 30 feet of corners in minutes by setting your 7" or 10" box to #3. Levelline Drywall Corner uses 30 – 50% less mud than bead. Never run out of mud while boxing the corner!

## DOUBLE BARREL HOPPER

The CertainTeed Double Barrel Hopper allows you to install Outside 90 in no time. You won't need to make adjustments or use extra hardware.

## SANDING

For dry sanding use 150 grit sand paper or finer. Lightly sand imperfections while being careful to avoid scuffing the paper. When dry sanding, wear a NIOSH approved dust mask and eye protection.

## Decoration

Ensure that all surfaces to be decorated are thoroughly dry and dust free. Either a good quality drywall primer or an undiluted latex wall paint with a high solids content should be applied prior to painting, texturing or wallpapering. Adhere to all manufacturers' specific directions for painting and decorating materials.

## Cleaning

Clean tools immediately after each use with warm, soapy water then wipe the tool surfaces dry to prevent rust. Leftover compound should be sealed and stored appropriately.

## Storage

Protect from excess moisture. Rotate stock.

## SDS

Safety Data Sheets are available on our web site, [certainteed.com](http://certainteed.com).

## Warning

Dust generated from sanding joint compound may cause eye, skin, nose, throat or respiratory irritation. Use wet-sanding to avoid creating dust. Avoid inhalation of dust and eye contact. Joint compound may contain silica. Inhalation of respirable silica dust can cause silicosis, a potentially disabling lung disease, known to cause lung cancer.

When sanding, drilling or abrading product during installation or handling: (1) Ensure adequate ventilation. (2) Wear a dust mask or, if dust may exceed PEL, use NIOSH/MSHA approved respirator. (3) Warn others in area. (4) Wear eye protection. If eye contact occurs, flush with lukewarm, gently flowing water for 5 minutes or until particle/dust is removed.

For further information, refer to Safety Data Sheet or consult manufacturer by calling 1-800-233-8990.

**KEEP OUT OF REACH OF CHILDREN.**

## Warranty

For product warranty information visit [certainteed.com/warranty](http://certainteed.com/warranty).

## Certifications

USGBC and the related logo are trademarks owned by the U.S. Green Building Council and are used with permission.



The Health Product Declaration® logo is a trademark or service mark of Health Product Declaration Collaborative, Inc., in the United States and in other countries and is being used herein under license.



## BIM/CAD INFORMATION

The BIM and CAD UL fire rated assemblies and sound assemblies can be found on CertainTeed's BIM and CAD Design Studio at [bimlibrary.saint-gobain.com/certainteed](http://bimlibrary.saint-gobain.com/certainteed). CertainTeed's BIM and CAD Design Studio provides BIM and CAD details to many UL fire rated assemblies and sound assemblies in easy to view experience. Plus, downloadable Revit and DWG and PDF CAD Details are available.

## SUSTAINABILITY

Sustainable documentation, including recycled content, EPD's, HPD's, VOC Certifications, can be found at [saintgobain.ecomedes.com](http://saintgobain.ecomedes.com).

## NOTICE

The information in this document is subject to change without notice. CertainTeed assumes no responsibility for any errors that may inadvertently appear in this document.

For Fire Resistance, no warranty is made other than conformance to the standard under which the assembly was tested. Minor discrepancies may exist in the values of ratings, attributable to changes in materials and standards, as well as differences between testing facilities. Assemblies are listed as "combustible" (wood framing) and "noncombustible" (concrete and/or steel construction).