

Product category: PRO300 (3" flange RedHeader PRO) As Jamb
Product name: 600PRO300-97 (50ksi, CP60) - Punched
 97mils (12ga) Coating: CP60 per ASTM C955

Geometric Properties

Web depth	6.000 in	Design thickness	0.1017 in
Flange width	3.000 in	Min. steel thickness	0.0966 in
Stiffening lip	1.000 in	Yield strength, Fy	50 ksi

Gross Section Properties of Full Section, Strong Axis

Cross sectional area (A)	1.347 in ²
Member weight per foot of length	4.58 lb/ft
Moment of inertia (Ix)	7.748 in ⁴
Section modulus (Sx)	2.583 in ³
Radius of gyration (Rx)	2.398 in
Gross moment of inertia (Iy)	1.742 in ⁴
Gross section modulus (Sy)	0.899 in ³
Gross radius of gyration (Ry)	1.137 in

Effective Section Properties, Strong Axis

Moment of inertia for deflection (Ixe)	7.748 in ⁴
Section modulus (Sxe)	2.551 in ³
Allowable bending moment (Max - Local)	84.28 in-k
Allowable bending moment (Max - Distortional)	74.42 in-k
Allowable shear force in web (Vax)	3805 lb

Torsional Properties

St. Venant torsion constant (J x 1000)	4.644 in ⁴
Warping constant (Cw)	15.243 in ⁶
Distance from shear center to neutral axis (Xo)	-2.516 in
Radii of gyration (Ro)	3.657 in
Torsional flexural constant (Beta)	0.527

Unbraced length (Lu) 65.5 in

ASTM & Code Standards:

- AISI S100-12 and S100-07 w/S2-10 supplements
- Effective properties incorporate the strength increase from cold work of forming
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- SDS & Product Certification Information is available at www.clarkdietrich.com


Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

05.40.00 (Cold-Formed Metal Framing)



RedHeader PRO™ Jamb

- Eliminates and/or minimizes built-up jams.
- Reduces material pieces, weight & screws.
- Opened jamb does not require pre-insulating.



Project Information

Name:
Address:

Contractor Information

Name:
Contact:
Phone:
Fax:

Architect Information

Name:
Contact:
Phone:
Fax: