

# **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

**Product category:** PRO350 (3-1/2" flange RedHeader PRO) As Jamb

Product name: 600PRO350-97 (50ksi, CP60) - Punched

97mils (12ga) Coating: CP60 per ASTM C955

#### **Geometric Properties**

Web depth	6.000 in	Design thickness	0.1017 in
Flange width	3.500 in	Min. steel thickness	0.0966 in
Stiffening lip	1.000 in	Yield strength, Fy	50 ksi

## **Gross Section Properties of Full Section, Strong Axis**

Cross sectional area (A)	1.449 in <sup>2</sup>
Member weight per foot of length	4.93 lb/ft
Moment of inertia (Ix)	8.633 in <sup>4</sup>
Section modulus (Sx)	2.878 in <sup>3</sup>
Radius of gyration (Rx)	2.441 in
Gross moment of inertia (Iy)	2.518 in⁴
Gross section modulus (Sy)	1.131 in <sup>3</sup>
Gross radius of gyration (Ry)	1.318 in

## **Effective Section Properties, Strong Axis**

Moment of inertia for deflection (Ixe)	8.632 in <sup>4</sup>
Section modulus (Sxe)	2.594 in <sup>3</sup>
Allowable bending moment (Max - Local)	77.65 in-k
Allowable bending moment (Max - Distortional)	78.38 in-k
Allowable shear force in web (Vax)	3805 lb

# **Torsional Properties**


St. Venant torsion constant (J x 1000)	4.994 in <sup>4</sup>
Warping constant (Cw)	21.811 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-2.979 in
Radii of gyration (Ro)	4.071 in
Torsional flexural constant (Beta)	0.464

### **ASTM & Code Standards:**

Unbraced length (Lu)

- $\bullet$  AISI S100-12 and S100-07 w/S2-10 supplements
- Effective properties incorporate the strength increase from cold work of forming
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- SDS & Product Certification Information is available at www.clarkdietrich.com

#### 05.40.00 (Cold-Formed Metal Framing)



- Eliminates and/or minimizes built-up jambs.
- · Reduces material pieces, weight & screws.
- · Opened jamb does not require pre-insulating.



### **Sustainability Credits:**

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

74.4 in

**LEED 2009 Credit MR 2 & MR 4** -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	<b>Contractor Information</b>	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:
		CD-RHPRO-J © 06/01/16 ClarkDietrich