

Product category: S137 (1-3/8" Flange Structural Stud)
Product name: **400S137-68 (50ksi, CP60) P - Punched**
68mils (14ga) Coating: CP60 per ASTM C955
Color coding: Orange

Geometric Properties

Web depth	4.000 in		
Flange width	1.375 in	Punchout width	1.50 in
Stiffening lip	0.375 in	Punchout length	4.00 in
Design thickness	0.0713 in	Min. steel thickness	0.0677 in
Yield strength, Fy	50 ksi	Fy with Cold-Work, Fya	50.0 ksi
Ultimate, Fu	65.0 ksi		

Gross Section Properties of Full Section, Strong Axis

Cross sectional area (A)	0.497 in ²
Member weight per foot of length	1.69 lb/ft
Moment of inertia (Ix)	1.165 in ⁴
Section modulus (Sx)	0.583 in ³
Radius of gyration (Rx)	1.531 in
Gross moment of inertia (Iy)	0.112 in ⁴
Gross radius of gyration (Ry)	0.475 in

Effective Section Properties, Strong Axis

Effective Area (Ae)	0.357 in ²
Moment of inertia for deflection (Ix)	1.165 in ⁴
Section modulus (Sx)	0.558 in ³
Allowable bending moment (Ma)	16.70 in-k
Allowable moment based on distortion buckling (Mad)	17.44 in-k
Allowable shear force in web (solid section)	4871 lb
Allowable shear force in web (perforated section)	1356 lb
Unbraced length (Lu)	27.6 in

Torsional Properties

St. Venant torsion constant (J x 1000)	0.842 in ⁴
Warping constant (Cw)	0.375 in ⁶
Distance from shear center to neutral axis (Xo)	-0.922 in
Distance between shear center and web centerline (m)	0.574 in
Radii of gyration (Ro)	1.850 in
Torsional flexural constant (Beta)	0.751

ASTM & Code Standards:

- AISI North American Specification [NASPEC] S100-12
- * Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at tools.clarkdietrich.com


Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).


LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

05.40.00 (Cold-Formed Metal Framing)



Used in framing applications:

- Load-bearing walls
- Curtain walls
- Tall interior walls
- Floor & ceiling joists
- Trusses



Structural Punchout

East market punchout spacing:
12" from lead end then 24" o.c.

West market punchout spacing:
24" from lead end then 24" o.c.

Project Information

Name:
Address:

Contractor Information

Name:
Contact:
Phone:
Fax:

Architect Information

Name:
Contact:
Phone:
Fax: