

Product Submittal Sheet

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product category: S250 (2-1/2" Flange Structural Stud)
Product name: 400S250-68 (50ksi, CP60) P - Punched

68mils (14ga) Coating: CP60 per ASTM C955

Fy with Cold-Work, Fya

Color coding: Orange

1.50 in 4.00 in

0.0677 in

50.0 ksi

Geometric Properties

Web depth 4.000 in
Flange width 2.500 in Punchout width
Stiffening lip 0.625 in Punchout length
Design thickness 0.0713 in Min. steel thickness

Yield strength, Fy 50 ksi Ultimate, Fu 65.0 ksi

Gross Section Properties of Full Section, Strong Axis

Cross sectional area (A)	0.693 in ²
Member weight per foot of length	2.36 lb/ft
Moment of inertia (Ix)	1.865 in⁴
Section modulus (Sx)	0.932 in ³
Radius of gyration (Rx)	1.640 in
Gross moment of inertia (Iy)	0.599 in⁴
Gross radius of gyration (Ry)	0.929 in

Effective Section Properties, Strong Axis

Effective Area (Ae)	0.463 in ²
Moment of inertia for deflection (Ix)	1.865 in⁴
Section modulus (Sx)	0.775 in ³
Allowable bending moment (Ma)	23.20 in-k
Allowable moment based on distortion buckling (Mad)	24.77 in-k
Allowable shear force in web (solid section)	4871 lb
Allowable shear force in web (perforated section)	1356 lb
Unbraced length (Lu)	51.6 in

Torsional Properties

St. Venant torsion constant (J x 1000)	1.174 in⁴
Warping constant (Cw)	2.225 in ⁶
Distance from shear center to neutral axis (Xo)	-2.105 in
Distance between shear center and web centerline (m)	1.235 in
Radii of gyration (Ro)	2.826 in
Torsional flexural constant (Beta)	0.445

ASTM & Code Standards:

- AISI North American Specification [NASPEC] S100-12
- * Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).


LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

WEB DEPTH WEB DEPTH X X X Structural Stud

05.40.00 (Cold-Formed Metal Framing)

Used in framing applications:

- Load-bearing walls
- Curtain walls
- Tall interior walls
- Floor & ceiling joists
- Trusses



Structural Punchout

East market punchout spacing: 12" from lead end then 24" o.c.

West market punchout spacing: 24" from lead end then 24" o.c.

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:
		CD-STRS © 07/18 ClarkDietrich Building Systems