

Product Submittal Sheet

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product category: S250 (2-1/2" Flange Structural Stud)
Product name: 925S250-43 (33ksi, CP60) P - Punched

43mils (18ga) Coating: CP60 per ASTM C955

Color coding: Yellow

Geometric Properties

Web depth 9.250 in Flange width 2.500 in Punchout width 1.50 in 4.00 in Stiffening lip 0.625 in Punchout length Design thickness 0.0451 in Min. steel thickness 0.0428 in Yield strength, Fy Fy with Cold-Work, Fya 33.0 ksi 33 ksi

Ultimate, Fu 45.0 ksi

Gross Section Properties of Full Section, Strong Axis

Cross sectional area (A)	0.684 in ²
Member weight per foot of length	2.33 lb/ft
Moment of inertia (Ix)	8.476 in⁴
Section modulus (Sx)	1.833 in ³
Radius of gyration (Rx)	3.521 in
Gross moment of inertia (ly)	0.520 in ⁴
Gross radius of gyration (Ry)	0.872 in

Effective Section Properties, Strong Axis

Effective Area (Ae)	0.301 in ²
Moment of inertia for deflection (Ix)	8.474 in⁴
Section modulus (Sx)	1.503 in ³
Allowable bending moment (Ma)	29.69 in-k
Allowable moment based on distortion buckling (Mad)	25.62 in-k
Allowable shear force in web (solid section)	905 lb
Allowable shear force in web (perforated section)	905 lb
Unbraced length (Lu)	61.0 in


Torsional Properties

St. Venant torsion constant (J x 1000)	0.464 in ⁴
Warping constant (Cw)	8.801 in ⁶
Distance from shear center to neutral axis (Xo)	-1.573 in
Distance between shear center and web centerline (m)	0.991 in
Radii of gyration (Ro)	3.954 in
Torsional flexural constant (Beta)	0.842

ASTM & Code Standards:


- AISI North American Specification [NASPEC] S100-12
- * Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

05.40.00 (Cold-Formed Metal Framing)



Used in framing applications:

- Load-bearing walls
- Curtain walls
- Tall interior walls
- Floor & ceiling joists
- Trusses



Structural Punchout

East market punchout spacing: 12" from lead end then 24" o.c.

West market punchout spacing: 24" from lead end then 24" o.c.

Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:
	Fax:	Fax:
		CD-STRS © 07/18 ClarkDietrich Building Syste