

# **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product category: S300 (3" Flange Structural Stud)

Product name: 800S300-97 (50ksi, CP60) P - Punched

97mils (12ga) Coating: CP60 per ASTM C955

Color coding: Red

### **Geometric Properties**

Web depth 8.000 in

Flange width 3.000 in Punchout width 1.50 in 4.00 in Stiffening lip 0.625 in Punchout length Design thickness 0.1017 in Min. steel thickness 0.0966 in Yield strength, Fy 50.0 ksi Fy with Cold-Work, Fya 50 ksi

Ultimate, Fu 65.0 ksi

### **Gross Section Properties of Full Section, Strong Axis**

Cross sectional area (A)	474 in²
Member weight per foot of length 5.0	02 lb/ft
Moment of inertia (Ix)	1.379 in⁴
Section modulus (Sx) 3.5	595 in³
Radius of gyration (Rx) 3.	123 in
Gross moment of inertia (ly) 1.5	595 in⁴
Gross radius of gyration (Ry)	040 in

### **Effective Section Properties, Strong Axis**

Effective Area (Ae)	0.887 in <sup>2</sup>
Moment of inertia for deflection (Ix)	14.172 in⁴
Section modulus (Sx)	3.304 in <sup>3</sup>
Allowable bending moment (Ma)	98.93 in-k
Allowable moment based on distortion buckling (Mad)	89.93 in-k
Allowable shear force in web (solid section)	10885 lb
Allowable shear force in web (perforated section)	5938 lb
Unbraced length (Lu)	58.1 in


#### **Torsional Properties**

St. Venant torsion constant (J x 1000)	5.082 in <sup>4</sup>
Warping constant (Cw)	20.304 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-2.017 in
Distance between shear center and web centerline (m)	1.243 in
Radii of gyration (Ro)	3.861 in
Torsional flexural constant (Beta)	0.727

#### **ASTM & Code Standards:**


- AISI North American Specification [NASPEC] S100-12
- \* Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

# 05.40.00 (Cold-Formed Metal Framing)



## **Used in framing applications:**

- Load-bearing walls
- Curtain walls
- Tall interior walls
- Floor & ceiling joists
- Trusses



Structural Punchout

East market punchout spacing: 12" from lead end then 24" o.c.

West market punchout spacing: 24" from lead end then 24" o.c.

#### **Sustainability Credits:**

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

**LEED v4 MR Credit** -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

**LEED 2009 Credit MR 2 & MR 4** -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	<b>Contractor Information</b>	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:
		CD-STRS © 07/18 ClarkDietrich Building System