

# **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product category: T1	T125 (1-1/4" Leg Structural Track)		05.40.00 (Cold-Formed Metal Fram	ning)
Product name: 10	00T125-54 (50ksi, CP60) - Unj	<b>cunched</b> : CP60 per ASTM C955		
Geometric Properties Web depth 10.198 in				Track
Leg width1.25 inDesign thickness0.0566 inYield strength, Fy50 ksiUltimate, Fu65.0 ksi	Min. steel thickness *Fy with Cold-Work, Fya	0.0538 in 50.0 ksi		Structural Tra
<b>Gross Section Propertie</b>	s of Full Section, Strong	Axis		nc.
Cross sectional area (Å) Member weight per foot of len Moment of inertia (Ix) Section modulus (Sx) Radius of gyration (Rx)		0.707 in <sup>2</sup> 2.41 lb/ft 8.337 in <sup>4</sup> 1.635 in <sup>3</sup> 3.434 in 0.059 in <sup>4</sup>	(t)	Str
Gross moment of inertia (ly) Gross radius of gyration (Ry)		0.288 in	Used in framing applications:	
Effective Section Prope	rties, Strong Axis		Load-bearing walls	
Effective Area (Ae) Moment of inertia for deflectio Section modulus (Sx)		0.240 in <sup>2</sup> 7.480 in <sup>4</sup> 1.055 in <sup>3</sup>	Curtain walls Tall interior walls Elect & coiling joints	

- Floor & ceiling joists
- Trusses

Effective Area (Ae)	0.240 in <sup>2</sup>
Moment of inertia for deflection (Ix)	7.480 in <sup>4</sup>
Section modulus (Sx)	1.055 in <sup>3</sup>
Allowable bending moment (Ma)	31.59 in-k
Allowable shear force in web	1628 lb

### **Torsional Properties**

St. Venant torsion constant (J x 1000) 0.75	55 in <sup>4</sup>
Warping constant (Cw) 1.21	12 in <sup>6</sup>
Distance from shear center to neutral axis (Xo) -0.3	76 in
Distance between shear center and web centerline (m) 0.25	56 in
Radii of gyration (Ro) 3.46	57 in
Torsional flexural constant (Beta) 0.98	38

## **ASTM & Code Standards:**

- AISI North American Specification [NASPEC] S100-12
- \* Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003 ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

#### Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- Clark Dietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:
1		

