

# **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

T125 (1-1/4" Leg Structural Track) **Product category:** 

**Product name:** 1000T125-97 (50ksi, CP60) - Unpunched

97mils (12ga) Coating: CP60 per ASTM C955

Color coding: Red

### **Geometric Properties**

Web depth 10.356 in Lea width 1.25 in

Design thickness 0.1017 in Min. steel thickness 0.0966 in Yield strength, Fy 50 ksi \*Fy with Cold-Work, Fya 50.0 ksi

Ultimate, Fu 65.0 ksi

### **Gross Section Properties of Full Section, Strong Axis**

Moment of inertia (Ix)  Section modulus (Sx)  Radius of gyration (Rx)  Gross moment of inertia (Iy)  15.083  2.913 i  3.448 i  0.100 i	Cross sectional area (A)	1.269 in <sup>2</sup>
Section modulus (Sx)  Radius of gyration (Rx)  Gross moment of inertia (ly)  2.913 i  3.448 i  0.100 i	Member weight per foot of length	4.32 lb/ft
Radius of gyration (Rx)  Gross moment of inertia (ly)  3.448 i 0.100 i	Moment of inertia (Ix)	15.083 in⁴
Gross moment of inertia (ly) 0.100 i	Section modulus (Sx)	2.913 in <sup>3</sup>
	Radius of gyration (Rx)	3.448 in
Gross radius of gyration (Ry) 0.281 i	Gross moment of inertia (Iy)	0.100 in⁴
	Gross radius of gyration (Ry)	0.281 in

### **Effective Section Properties, Strong Axis**

Effective Area (Ae)	0.695 in <sup>2</sup>
Moment of inertia for deflection (Ix)	15.077 in⁴
Section modulus (Sx)	2.753 in <sup>3</sup>
Allowable bending moment (Ma)	82.42 in-k
Allowable shear force in web	9507 lb

### **Torsional Properties**

St. Venant torsion constant (J x 1000)	4.375 in <sup>4</sup>
Warping constant (Cw)	2.123 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-0.363 in
Distance between shear center and web centerline (m)	0.247 in
Radii of gyration (Ro)	3.478 in
Torsional flexural constant (Beta)	0.989

### **ASTM & Code Standards:**

- AISI North American Specification [NASPEC] S100-12
- \* Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- · ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

### **Sustainability Credits:**

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

Fax:

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 - ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

# (t)

05.40.00 (Cold-Formed Metal Framing)

## **Used in framing applications:**

- Load-bearing walls
- Curtain walls
- Tall interior walls
- Floor & ceiling joists
- Trusses

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:

Fax:

CD-STRT © 07/18 ClarkDietrich Building Systems