

## **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product catego	ory: T15	T150 (1-1/2" Leg Structural Track)			05.40.00 (Cold-Formed Met
Product name:	600	T150-43 (33ks	si, CP60) - Unpu	inched	Y
	43m	ils (18ga)	Coating: Color coding:	CP60 per ASTM C955 Yellow	
<b>Geometric Pro</b>	perties				
Web depth Leg width	6.161 in 1.5 in				
Design thickness	-	Min. stee	l thickness	0.0428 in	E
Yield strength, Fy	33 ksi	*Fy with (	Cold-Work, Fya	33.0 ksi	
Ultimate, Fu	45.0 ksi				\$ \$ \$
<b>Gross Section</b>	Properties	of Full Sec	tion, Strong	Axis	
Cross sectional area (A)				0.405 in <sup>2</sup>	
Member weight per foot of length				1.38 lb/ft	(t)
Moment of inertia (Ix)				2.073 in <sup>4</sup>	
Section modulus (Sx)				0.673 in <sup>3</sup>	Y
Radius of gyration (Rx)				2.261 in	
Gross moment of inertia (ly)				0.073 in <sup>4</sup>	
Gross radius of gyration (Ry)				0.424 in	Used in framing applicati
Effective Section	on Propert	ies Strong	Avis		<ul> <li>Load-bearing walls</li> </ul>
		lies, serong	0.184 in <sup>2</sup>	<ul> <li>Curtain walls</li> </ul>	
Effective Area (Ae) Moment of inertia for deflection (Ix)				1.890 in <sup>4</sup>	<ul> <li>Tall interior walls</li> </ul>
Section modulus (Sx)				0.474 in <sup>3</sup>	
Allowable bending moment (Ma)				9.36 in-k	<ul> <li>Floor &amp; ceiling joists</li> </ul>
, monuble bending		•)		0.00 11 1	<b>T</b>

Allowable shear force in web **Torsional Properties** 

Torsional Properties	
St. Venant torsion constant (J x 1000)	0.275 in⁴
Warping constant (Cw)	0.504 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-0.680 in
Distance between shear center and web centerline (m)	0.437 in
Radii of gyration (Ro)	2.399 in
Torsional flexural constant (Beta)	0.920

## **ASTM & Code Standards:**

- AISI North American Specification [NASPEC] S100-12
- \* Effective properties incorporate the strength increase from the cold work of forming
- · Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003 ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance
- Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

## Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED


LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

1377 lb

LEED 2009 Credit MR 2 & MR 4 -- Clark Dietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

## etal Framing)



tions:

- Floor & ceiling joists
- Trusses