Product Submittal Sheet

Technical Services: 888-437-3244
Engineering Services: 877-832-3206
Sales: 800-543-7140
clarkdietrich.com

Product category: T150 (1-1/2" Leg Structural Track)
Product name: **1350T150-68 (50ksi, CP60) - Unpunched**
68mils (14ga)
Coating: CP60 per ASTM C955
Color coding: Orange

05.40.00 (Cold-Formed Metal Framing)



Structural Track

Geometric Properties

Web depth	13.750 in		
Leg width	1.5 in		
Design thickness	0.0713 in	Min. steel thickness	0.0677 in
Yield strength, Fy	50 ksi	*Fy with Cold-Work, Fya	50.0 ksi
Ultimate, Fu	65.0 ksi		

Gross Section Properties of Full Section, Strong Axis

Cross sectional area (A)	1.175 in^2
Member weight per foot of length	4.00 lb/ft
Moment of inertia (Ix)	24.573 in^4
Section modulus (Sx)	3.574 in^3
Radius of gyration (Rx)	4.572 in
Gross moment of inertia (Iy)	0.129 in^4
Gross radius of gyration (Ry)	0.332 in

Effective Section Properties, Strong Axis

Effective Area (Ae)	0.380 in^2
Moment of inertia for deflection (Ix)	21.859 in^4
Section modulus (Sx)	2.261 in^3
Allowable bending moment (Ma)	67.69 in-k
Allowable shear force in web	2409 lb

Torsional Properties

St. Venant torsion constant (J x 1000)	1.992 in^4
Warping constant (Cw)	4.933 in^6
Distance from shear center to neutral axis (Xo)	-0.417 in
Distance between shear center and web centerline (m)	0.286 in
Radii of gyration (Ro)	4.603 in
Torsional flexural constant (Beta)	0.992

Used in framing applications:

- **Load-bearing walls**
- **Curtain walls**
- **Tall interior walls**
- **Floor & ceiling joists**
- **Trusses**

ASTM & Code Standards:

- AISI North American Specification [NASPEC] S100-12
- * Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

Sustainability Credits:
For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED
LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).
LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

CD-STRT © 07/18 ClarkDietrich Building Systems