


Technical Services: 888-437-3244, Engineering Services: 877-832-3206, Sales 800-543-7140

## 05.40.00 (Cold-Formed Metal Framing)

## 600T200-43 (33ksi, CP60)

600T200-43 (33ksi, CP60) 600 (6") structural track with T200 (2") leg - 43mils (18ga)		
Coating: CP60 per AISI S240		Color Code: Yellow
Geometric Proper	rties	
Web depth: 6.161 in Leg width: 2.00 in	Thickness: 43mils (18ga) Design Thickness: 0.0451 in Min. steel thickness: 0.0428 in	Yield strength, Fy: 33 ksi *Fy with Cold-Work, Fya: 33.0 ksi Ultimate, Fu: 45.0 ksi
Gross Section Properties of Full Section, Strong Axis		
Cross sectional area (A)		0.451 in <sup>2</sup>
Member weight per foot of length		1.53 lb/ft
Moment of inertia (Ix)		2.494 in <sup>4</sup>
Section Modulus (Sx)		0.810in <sup>3</sup>
Radius of gyration (Rx)		2.353 in
Gross moment of inerita (ly)		0.163 in <sup>4</sup>
Gross radius of gyration (Ry)		0.602 in
	Effective Section Properties,	Strong Axis
Effective Area (Ae)		0.186 in <sup>2</sup>
Moment of inertia for deflection (lx)		2.076 in <sup>4</sup>
Section modulus (Sx)		0.565 in <sup>3</sup>
Allowable bending moment (Ma)		11.16 in-k
Allowable shear force in web		1377 lb
	Torsional Properti	es
St. Venant torsional constant (J x 1000)		0.305 in <sup>4</sup>
Warping constant (Cw)		1.098 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)		-1.044 in
Distance between shear center and web centerline (m)		0.652 in
Radii of gyration (Ro)		2.644 in
Torsional flexural constant (Beta)		0.844
Effective properties in	corporate the strength increase from t	the cold work of forming



Load-bearing walls

Curtain walls

Tall interior walls

- · Floor & ceiling joists
- Trusses



• Effective properties incorporate the strength increase from the cold work of forming.

## **Code Approvals & Performance Standards**

- AISI S100-16 (2020) w/S2-20 North American Specification for the Design of Cold-Formed Steel Structural Members
- AISI S240-20 North American Standard for Cold-Formed Steel Structural Framing
- (Compliant to ASTM C955, but IBC replaced with AISI S200 in IBC 2015, AISI S240 in IBC 2018)
- Section A3 Material Chemical & mechanical requirements (Referencing ASTM A1003/A1003M)
- Section A4 Corrosion Protection (Referencing ASTM A653/A653M)
- Section A5 Products Thickness, shapes, tolerances, identification
- Section C Installation (Referencing ASTM C1007)
- IBC 2021 International Building Code
- ICC-ES ESR-1166P Structural Studs and Track
- ESR-1166P LABC and LARC Supplement
- ESR-1166P Catalog ClarkDietrich Structural Technical Design Guide (6/22/20)
- Intertek CCRR-0206 Structural Studs and Track
- SFIA Stud Code Compliance Certification Program
- SDS For ASTM A1003 Steel Framing Products For Interior Framing, Exterior Framing and Clips/Accessories

**Sustainability Credits** For more details and LEED letters contact Technical Services at 888-437-3244 or visit clarkdietrich.com/LEED.

- LEED v4.1 MR Credit: Environmental Product Declarations: EPD (1 point) - Sourcing of Raw Materials (up to 2 points) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points)
- LEED v4 MR Credit: Building Product Disclosure and Optimization: EPD (1 point) -Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) -Innovation Credit (up to 2 points).