

Product Submittal Sheet

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product catego	ory: T250	T250 (2-1/2" Leg Structural Track)		05.40.00 (Cold-Formed Metal Fram
Product name:	1400	T250-97 (50ksi, CP60) - Unp ils (12ga) Coating: Color coding:	CP60 per ASTM C955	
Geometric Pro	perties	C C		
Web depth	14.356 in			
Leg width	2.5 in			m
Design thickness	0.1017 in	Min. steel thickness	0.0966 in	E oo oo
Yield strength, Fy	50 ksi	*Fy with Cold-Work, Fya	50.0 ksi	
Ultimate, Fu	65.0 ksi	, , ,		₩ <mark>- xo</mark>
Gross Section	Properties	of Full Section, Strong	Axis	
Cross sectional ar		,	1.930 in ²	
Member weight per foot of length			6.57 lb/ft	(1)
			48.957 in⁴	
Section modulus (Sx)			6.821 in ³	\$
Radius of gyration (Rx)			5.036 in	LEG WIDTH
Gross moment of inertia (Iy)			0.803 in ⁴	
Gross radius of gy	ration (Ry)		0.645 in	Used in framing applications:
Effective Section	on Propert	ies, Strong Axis		 Load-bearing walls
Effective Area (Ae			0.773 in ²	Curtain walls
Moment of inertia		(1x)	44.895 in ⁴	Tall interior walls
Section modulus (4.708 in ³	
Allowable bending moment (Ma)		140.96 in-k	 Floor & ceiling joists 	

Trusses

0.773 in ²
44.895 in ⁴
4.708 in ³
140.96 in-k
6761 lb

Torsional Properties

St. Venant torsion constant (J x 1000)	6.654 in⁴ 31.333 in⁵
Warping constant (Cw) Distance from shear center to neutral axis (Xo)	-0.938 in
Distance between shear center and web centerline (m)	0.622 in
Radii of gyration (Ro)	5.163 in
Torsional flexural constant (Beta)	0.967

ASTM & Code Standards:

- AISI North American Specification [NASPEC] S100-12
- * Effective properties incorporate the strength increase from the cold work of forming
- · Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003 ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- Clark Dietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

ming)

