

# **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

Product category: Product name:		T350 (3-1/2" Leg Structural Track)			05.40.00 (Cold-Formed Metal Framing)	
		1150T350-68 (50ksi, CP60) - Unp		unched	Y	
		ooniiis (14ga)	Coating: Color coding:	: CP60 per ASTM C955 : Orange		
<b>Geometric Pro</b>	perties	5				Track
Web depth	11.750	) in				ac
Leg width	3.5 in				m	
Design thickness	0.0713	3 in Min. steel	thickness	0.0677 in	H SC CG	
Yield strength, Fy	50 ksi	*Fy with C	Cold-Work, Fya	50.0 ksi		ไล
Ultimate, Fu	65.0 k	si			× - ×	tu
Gross Section	Proper	ties of Full Sec	tion, Strong	Axis		Structural
Cross sectional area (A)				1.318 in <sup>2</sup>		E.
Member weight per foot of length				4.48 lb/ft	(t)	<b>S</b>
Moment of inertia (Ix) 26.014 in <sup>4</sup>						
Section modulus (Sx)				4.428 in <sup>3</sup>	Y	
Radius of gyration (Rx)				4.443 in		
				1.420 in⁴		_
Gross radius of gy	ration (F	Ry)		1.038 in	Used in framing applications:	
Effective Section	on Pro	perties, Strong	Axis		<ul> <li>Load-bearing walls</li> </ul>	
Effective Section Properties, Strong AxisEffective Area (Ae)0.395 in²					<ul> <li>Curtain walls</li> </ul>	
Moment of inertia for deflection (Ix)				21.130 in <sup>4</sup>	<ul> <li>Tall interior walls</li> </ul>	
Section modulus (Sx)				2.175 in <sup>3</sup>	• Electr 8 colling joints	
Allowable bending moment (Ma)				65.13 in-k	<ul> <li>Floor &amp; ceiling joists</li> </ul>	
Allowable shear force in web				2832 lb	• Trusses	

### **Torsional Properties**

St. Venant torsion constant (J x 1000)	2.233 in⁴
Warping constant (Cw)	35.026 in <sup>6</sup>
Distance from shear center to neutral axis (Xo)	-1.759 in
Distance between shear center and web centerline (m)	1.109 in
Radii of gyration (Ro)	4.890 in
Torsional flexural constant (Beta)	0.871

## **ASTM & Code Standards:**

- AISI North American Specification [NASPEC] S100-12
- \* Effective properties incorporate the strength increase from the cold work of forming
- Gross properties are based on the cross section away from the punchouts
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003 ClarkDietrich's structural and nonstructural framing comply with the SFIA Code Compliance
- Certification Program, ICC-ES ESR-1166P and Intertek CCRR-0206
- For installation & storage information refer to ASTM C1007
- SDS & Product Certification Information is available at itools.clarkdietrich.com

#### Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- Clark Dietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

