

## **Product Submittal Sheet**

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

### TradeReady® Rim Track

Product category	7-1/4" 18ga TradeReady Rim Track with preformed tabs
Product name	725TD250-43 (33ksi) - w/ tabs
Finish	CP60

#### **Geometric Properties**

Inside Web depth	7.250 in	Design thickness	0.0451 in
Top leg width	1.250 in	Min. steel thickness	0.0428 in
Bottom leg width	2.500 in	Yield stress, Fy	33 ksi
Tab depth	4.000 in	Ultimate, Fu	45 ksi

#### **Gross Section Properties of Full Section**

Cross sectional area (A) Member weight per foot of length Moment of inertia (Ix) Section modulus (Sx) Gross moment of inertia (Iy)	0.493 in(^2) 1.612 lbs/ft 3.550 in(^4) 0.868 in(^3) 0.196 in(^4)
Section modulus (Sy)	0.092 in(^3)
Net Section Properties (at tab)	
Cross sectional area (A)	0.312 in(^2)
Moment of inertia (Ix)	3.260 in(^4)
Capacity at Tab Hole	

# Fully Braced Allowable Moment @ Hole when<br/>Small Flange is in Compression (Mpos)8829 in-lbsFully Braced Allowable Moment @ Hole when<br/>Large Flange is in Compression (Mneg)9040 in-lbsAllowable Shear at Tab Hole (Va)591 lbs

#### **Torsional Section Properties:**

Distance between centroid and shear-center (Xo)			
Distance between centroid and web-centerline (X)			
St. Venant torsional constant (J*1000)			
Torsional warping constant (Cw)			
Radii of gyration (Ro)			
Torsional flexural constant (Beta)			

#### **Product Data & Ordering Information:**

Length	12'-0" long pieces	
Tabs spaced at:	12", 16", 19.2" or 24" intervals	

#### **ASTM & Code Standards:**

- AISI North American Specification [NASPEC] 2004
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- SDS & Product Certification Information is available at www.clarkdietrich.com/SupportDocs
- U.S. Patent Nos. 6,301,854; 6,691,478; 6,418,694; 6,691,487; 6,761,005; 7,240,459

Canadian Patent No. 2319346, Mexican Patent No. 243294

#### Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

-0.738 in 0.350 in

3.500 in 1.060 in

0.000334 (in^4) 0.822 (in^6)

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).


LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)


Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

#### 05.40.00 (Cold-Formed Metal Framing)



Eliminates or drastically reduces support clips, joist hangers and web stiffeners
Sizes include 7-1/4", 8", 9-1/4", 10", 11-1/4", 12" and 14".





1.25