

Product Submittal Sheet

Technical Services: 888-437-3244 Engineering Services: 877-832-3206 Sales: 800-543-7140 clarkdietrich.com

TradeReady® Rim Track

Product category	7-1/4" 14ga TradeReady Rim Track with preformed tabs
Product name	725TD250-68 (50ksi) - w/ tabs
Finish	CP60

Geometric Properties

Inside Web depth	7.250 in	Design thickness	0.0713 in
Top leg width	1.250 in	Min. steel thickness	0.0677 in
Bottom leg width	2.500 in	Yield stress, Fy	50 ksi
Tab depth	4.000 in	Ultimate. Fu	65 ksi

Gross Section Properties of Full Section

Cross sectional area (A)	0.776 in(^2)
Member weight per foot of length	2.537 lbs/ft
Moment of inertia (Ix)	5.591 in(^4)
Section modulus (Sx)	1.358 in(^3)
Gross moment of inertia (ly)	0.305 in(^4)
Section modulus (Sy)	0.144 in(^3)
Net Section Properties (at tab)	
Cross sectional area (A)	0.490 in(^2)
Moment of inertia (Ix)	5.131 in(^4)
Capacity at Tab Hole	
Fully Braced Allowable Moment @ Hole when	
Small Flange is in Compression (Mpos)	26184 in-lbs
Fully Braced Allowable Moment @ Hole when	

Large Flange is in Compression (Mneg)27334 in-lbsAllowable Shear at Tab Hole (Va)2335 lbs

Torsional Section Properties:

Distance between centroid and shear-center (Xo)			
Distance between centroid and web-centerline (X)			
St. Venant torsional constant (J*1000)			
Torsional warping constant (Cw)			
Radii of gyration (Ro)			
Torsional flexural constant (Beta)			

Product Data & Ordering Information:

Length	12'-0" long pieces	
Tabs spaced at:	12", 16", 19.2" or 24" intervals	

ASTM & Code Standards:

- AISI North American Specification [NASPEC] 2004
- Structural framing is produced to meet or exceed ASTM C955
- Sheet steel meets or exceeds mechanical and chemical requirements of ASTM A1003
- SDS & Product Certification Information is available at www.clarkdietrich.com/SupportDocs
- U.S. Patent Nos. 6,301,854; 6,691,478; 6,418,694; 6,691,487; 6,761,005; 7,240,459

Canadian Patent No. 2319346, Mexican Patent No. 243294

Sustainability Credits:

For more details and LEED letters contact Technical Services at 888-437-3244 or visit www.clarkdietrich.com/LEED

-0.732 in 0.347 in

3.506 in 1.060 in

0.001314 (in^4) 1.265 (in^6)

LEED v4 MR Credit -- Building Product Disclosure and Optimization: EPD (1 point) - Sourcing of Raw Materials (1 point) - Material Ingredients (1 point) - Construction and Demolition Waste Management (up to 2 points) - Innovation Credit (up to 2 points).

LEED 2009 Credit MR 2 & MR 4 -- ClarkDietrich's steel products are 100% recyclable and have a national average recycled content of 34.2% (19.8% post-consumer and 14.4% pre-consumer). If seeking a higher number to meet Credit MR 5, please contact us at (info@clarkdietrich.com / 888-437-3244)

Project Information	Contractor Information	Architect Information
Name:	Name:	Name:
Address:	Contact:	Contact:
	Phone:	Phone:
	Fax:	Fax:

05.40.00 (Cold-Formed Metal Framing)



Eliminates or drastically reduces support clips, joist hangers and web stiffeners
Sizes include 7-1/4", 8", 9-1/4", 10", 11-1/4", 12" and 14".



