CONCRETE SEALERS USA

Professional Concrete Solutions You Can Trust

5 US Gallons

PS108 is an economical water based sodium silicate solution with a siliconate water and salt repellent additive that penetrates into an unsealed cementitious while retaining its breathability. It is an ideal treatment for machine troweled while retaining its breathaumity. It is an lobeal deathern to machine roweled, burnished, or polished concrete surfaces. Once the sealer chemically reacts with the surface, the PS108 improves the abrasion resistance and durability of a surface, provides long term protection against wear and traffic, reduces dusting not caused by actual surface defects, and lowers the overall maintenance of a surface. It also provides resistance to water and moisture, efforescence, dirt buildup, mold and mildew, and salts and deicing chemicals. It can also serve as a bolidate, filolo and filidew, and saits and declined prefileds. It can last series as a concrete polishing aid by producing better initial surface hardness that reduces polishing time and yields a smoother and denser burnished or polished surface. Sealer is environmentally friendly, VOC compliant, non-flammable, and has odorless formula for safe indoor use. PS108 has a clear appearance. Upon proper application, the substrate will have little, or no, noticeable change in appearance when dry. However, a polished appearance can normally be imparted to burnished or polished surfaces by applying with scrubber or polisher and then buffing with a

enjoy the same superior benefits that architects, engineers, and large contractors have enjoyed for years. PS108 is recommended as a densifier and hardener for machine troweled concrete surfaces. It can also be used on other cementitious surfaces where densifying and hardening benefits along with water repellent characteristics are desired. It is also recommended as a polishing aid for burnished or polished concrete surfaces. It is ideal for sealing commercial and residential concrete floors such as workshop floors, warehouse floors, automotive garage floors, tretail store floors, pole barn and shed floors, basement floors, garage floors, and other machine troweled, burnished, or polished concrete surfaces.

PS108 is designed to work only on cured machine troweled and smooth concrete surfaces and is not intended for asphalt. This product may damage vegetation or may etch glass, vinyl, aluminum, plastic, and metal. Avoid contact with eyes and skin. Sealer may be damaged if frozen prior to use. Not intended to seal cracks. Will not remediate structurally unsound surfaces with defects such as chronic dusting liability, other than replacement of defective product. A small test must be conducted prior to application. Based upon this test, the purchaser shall determine for themselves the suitability of this product for the intended use.

Environmental & Regulatory
PS108 compiles with EPA, FDA and OSHA strict requirements and contains no
solvents or Volatile Organic Compounds (VOC), This product is considered a
non-hazardous chemical under OSHA Hazard Communication Standard (290FR
1910.1200). Contact may cause skin or eye irritation. Using with adequate air
ventilation, eye protection, and gloves is recommended.

REFER TO SAFETY DATA SHEET PRIOR TO USE.

PS108 Sodium Silicate w/ Siliconate Densifier WB Penetrating Sealer

Zero VOC, Water Based Concrete Floor Densifier & Hardener

- Professional Grade
- One Step Application
- Dries Flat & Clear
- Densifies & Hardens
- Limits Dirt Buildup
- Protects Against Wear
- Resists Salts & Deicing Chemicals
- Restricts Water & Moisture Decreases Efflorescence & Dusting
 - **▶** Increases Surface Strength
 - Enhances Abrasion Resistance

Great for

Workshop Floors | Warehouse Floors | Automotive Garage Floors Retail Store Floors | Pole Barn & Shed Floors | Basement Floors | Garage Floors

Substrates to be sealed must be a minimum of 28 days old and/ or be fully cured. The surface must be clean and porous enough to allow penetration into the substrate. glease, pletitude scalars, curing ageins, plant or other softened coverings, in a direct contaminants. If acid or other cleaning compound is used for cleaning or etching the surface, neutralize the surface completely before application of PS108. Under certain conditions, a precipitate may be deposited as the sodium solution dries. Substrates with a high acidic level will react with the sodium solution and can cause some neutralization of the material before it is absorbed into the surface leaving a white precipitate. This white precipitate does not affect sealer performance and generall ites over time or remove with water and stiff broom or floor buffer. A test should be made to determine that none of these conditions exist.

Always test porosity prior to application, especially on very dense surfaces. Surface during the application or drying period. Apply uniformly with a low pressure spraye When applying material, work in small, manageable areas at a time in order to maintain a wet edge. Product should be applied to the point of rejection and be fully may result in white residue (especially on darker or colored surfaces) which will not affect sealer performance and generally dissipates over time or by power washing. White residue may also form if surface has high acidic content. To reduce likelihood of white residue on surface, rinse the surface thoroughly with water 2 hours after final application of sealer and then sweep up to remove any residual materials. Generally only one application is required. If additional coats are desired and more product can be absorbed, wait approximately 1-2 hours between coats. For a more polished appearance on burnished or polished surfaces, apply using a floor scrubber (black pad) or high speed polisher and then buff with a white pad after 12 hours. Clean

Under normal conditions the sealer will dry clear and flat. However, a polished appearance can normally be imparted to burnished or polished concrete surfaces by applying with scrubber or polisher and then buffing with a white pad. Polished appearance is based solely upon application procedure of the applicator.

Coverage Rate 300-400 sq. ft. per/Gal. for machine troweled and smooth surfaces. Coverage rates

Drying TimeDry to touch in 1-2 hours and for traffic in 12-24 hours. Drying times are for

Eyes: Flush with water for at least 15 minutes. Skin: Wash thoroughly with soap and water. Inhalation: Move subject to fresh air. Digestion: Consult physician immediately



Toll-Free: 888.583.2991 | Fax: 920.759.5100 | Emergency: 800.424.9300 info@concretesealersusa.com | www.concretesealersusa.com



