

## CRYSTALITE

PRODUCT CODE: SCRY

### PRODUCT

Crystalite (SCRY) translucent fiberglass reinforced plastic (FRP) panels are durable, semi-rigid, and will not mold, mildew, or corrode. Crystalite panels use an exterior grade Neopentyl Glycol (NPG) resin combined with random chopped fiberglass for reinforcement.

### PURPOSE

Crystalite panels are intended for use as a greenhouse or translucent architectural panel where UV stabilizers are required. The 5oz. Crystalite panels are Class C Fire Rated and are suitable for use when a Class C fire rating is required. ASTM-E84 is defined where building code requires flame spread  $\leq 200$  and smoke development  $\leq 450$ .

### DESIGN PROPERTIES

PRODUCT CODE	TYPE	WEIGHT	COLOR	LIGHT TRANSMISSION	SIZE
XXXSCRY xxx = PROFILE NUMBER	Translucent	4 oz./ft <sup>2</sup>	502 Clear 418 White 436 Translucent White	N/A	10" - 60" x 24" - up to 500'   4' x 10' (multiples may be required)
	Translucent	5 oz./ft <sup>2</sup>	502 Clear 418 White 436 Translucent White	N/A	10" - 60" x 24" - up to 500'   4' x 10' 48" x 50" Available in Stock - Clear (502) (multiples may be required)
	Translucent	8 oz./ft <sup>2</sup>	502 Clear 418 White 436 Translucent White	63 - 71 % (Translucent White   436) 92 - 100 % (Clear   502)	10" - 60" x 24" - 500' x 8'   4' x 10' (multiples may be required)

12,000 sq. ft. per product, weight and colors required to manufacture. Orders from different customers may be batched to obtain manufacturing minimums, however lead time may be affected.

\*Crystalite 5 oz. meets minimum requirements of major model building codes for Class C with requires a flame spread  $\leq 200$  and smoke development  $\leq 450$  (per ASTM E-84).

### TYPICAL PHYSICAL PROPERTIES

PROPERTY	SCRY 4oz./ft <sup>2</sup>	SCRY 5oz./ft <sup>2</sup>	SCRY 8oz./ft <sup>2</sup>	TEST METHOD
WEIGHT	0.25 lb/ft <sup>2</sup> 1.22 kg/m <sup>2</sup>	0.31 lb/ft <sup>2</sup> 1.53 kg/m <sup>2</sup>	0.50 lb/ft <sup>2</sup> 2.44 kg/m <sup>2</sup>	---
TENSILE STRENGTH	10.0 x 10 <sup>3</sup> psi 69 MPa	12 x 10 <sup>3</sup> psi 83 MPa	15 x 10 <sup>3</sup> psi 103 MPa	ASTM - D638
TENSILE MODULUS	1.2 x 10 <sup>6</sup> psi 8274 MPa	1.2 x 10 <sup>6</sup> psi 8274 MPa	1.4 x 10 <sup>6</sup> psi 9653 MPa	ASTM - D638
FLEXURAL STRENGTH	20 x 10 <sup>3</sup> psi 138 MPa	25 x 10 <sup>3</sup> psi 172 MPa	28 x 10 <sup>3</sup> psi 193 MPa	ASTM - D790
FLEXURAL MODULUS	0.9 x 10 <sup>6</sup> psi 6205 MPa	0.9 x 10 <sup>6</sup> psi 6205 MPa	1.0 x 10 <sup>6</sup> psi 6895 MPa	ASTM - D790

**TESTING**

Valto Engineered Materials (called VALTO hereafter) panels meet or exceed applicable requirements of the following standards:

1. ASTM D3841, Standard Specification for Glass Fiber Reinforced Polyester Plastic Panels.
2. Code requirements of most state, county and municipal building departments.
3. Valto Engineered Materials is a recognized UL90 component manufacturer.

**SPECIFICATIONS**

VALTO panels are manufactured by a continuous laminating process in lengths as required.

**COMPOSITION**

Reinforcement: Random Chopped fiberglass.

Resin Mix: Polyester/styrene copolymer, inorganic fillers, and pigments.

**FINISHED PANEL QUALITY**

1. Panels shall have a wear side with a smooth or textured finish. Color shall be uniform throughout as specified. The backside shall be smooth. The backside surface may have some variations which do not affect functional properties and are not cause for rejection.
2. Physical properties shall be as set forth on Page 1.
3. Dimensions shall be as specified on purchase order, subject to the following tolerances:
 

WIDTH:	±1/8" (±3.2 mm)
LENGTH:	±1/8" (±3.2 mm) up to 12" (3.7 m)
SQUARENESS:	±1/8" (3.2 mm) in 48" (1.2 m) of width
4. Product quality standards and tolerances for panel weight and thickness shall be as set forth in Valto Engineered Materials' Quality Control Procedures/Standards which are available on request.

**CERTIFICATIONS**

1. FRP does not support mold or mildew (per ASTM D3273 and ASTM D3274).
2. Crystalite 5 oz. meets minimum requirements of major model building codes for Class C with requires a flame spread ≤200 and smoke development ≤450 (per ASTM E-84). (Crystalite 4 oz. and 8 oz. have not been tested and should not be used as an interior panel).

**FABRICATING RECOMMENDATIONS**

NOTE: Protect your eyes with goggles; cover your nose and mouth with a filter mask; cover exposed skin when cutting VALTO panels.

HAND FABRICATING: Drilling—High speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

CUTTING: Sheet metal shears or circular saw with reinforced carborundum or carbide-tipped blade.

PRODUCTION FABRICATING: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed.

For irregular cuts, use die punch or band saw.

SDS: Prior to working with our products, see our most current SDS at [valtoem.com/sds](http://valtoem.com/sds)

**STORAGE RECOMMENDATIONS**

Store panels properly. While a single panel is engineered to withstand exposure to sunlight and the elements, a stack of panels will trap heat and moisture, causing internal clouding and/or yellowing in the panels. To avoid this irreversible effect, panels must be stored in a dry, shaded, well ventilated area. Skids should be elevated at one end by wood spacers. Failure to comply with recommended storage procedures will void the warranty on the panels.

**CAUTIONS AND SAFETY WARNINGS**

DO NOT WALK ON PANELS. Valto Engineered Materials panels are not intended to support the undistributed weight of workers. Roofing ladders or 1" x 12" planks, or equivalent means of protection must be used during any work on roofs. Provide fall protection in accordance with OSHA standard 29 CFR 1910 [see paragraph 1910.23(a)(4) AND (e)(8)]. Compliance with this regulation as well as any other local, state or federal safety requirements is the responsibility of the building owner, contractor and/or erector.

**MAINTENANCE**

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material does not provide an acceptable appearance, Valto Engineered Materials should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Valto Engineered Materials. Valto Engineered Materials' sole responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.

**FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS**

The numerical flame spread and smoke development ratings are not intended to reflect alleged hazards presented by VALTO products under actual fire conditions and this product has not been tested by VALTO except as set forth below. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test").

VALTO PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, FRP may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression system necessary for a specific installation. We believe all information given is accurate, without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents. [www.astm.org/Standards/E84.htm](http://www.astm.org/Standards/E84.htm).

At Valto, we partner with our customers, and through innovation, deliver advanced materials that enhance everyday environments. We succeed through a culture of collaboration, continuous improvement, and excellence. With integrity at our core, we challenge the status quo and pursue innovative approaches that benefit our customers and associates.

Since 1954, Valto Engineered Materials has provided innovative products and services and is a leading provider of FRP composite panels. Our lightweight composite products deliver unsurpassed strength and durability; and we continue to pioneer next level performance in building materials, recreational vehicles, and transportation.