



RETRO PEL™

CHEMICAL RESISTANCE TESTING SUMMARY (Oct. 7, 2003)

0 - 4 = Stain Scale (no stain, slight stain, stain, moderate stain, heavy stain)

0 - 4 = Etch Scale (no etch, slight etch, etch, moderate etch, heavy etch)

<i>Chemical</i>	<i>Stain</i>	<i>Etch</i>
Hydraulic Fluid	0	0
Automatic Transmission Fluid	0	0
Brake Fluid	0	0
Power Steering Fluid	0	0
Havoline SAE 30 HD Motor Oil	0	0
Pennzoil SAE HD 40 Motor Oil	0	0
Castrol MTX Synthetic SAE 80W	0	0
Prestone Antifreeze/Coolant	0	0
CRC STA-PLEX Premium Red Grease	0	0
Mineral Oil	0	0
Cola	0	1
Mustard	0	1
Bacon Grease	0	0
Ketchup	0	1
Wesson Oil	0	0
TOTAL	0	3