

TECHNICAL DATA SHEET

DESCRIPTION

Cure & Seal 30% J23WB is a water based, Earth Friendly (EF) non-yellowing 30% solids acrylic copolymer curing and sealing compound that may contribute to LEED Credits. The Cure & Seal 30% J23WB formula is low odor and contains VOC < 100 g/L, making it VOC compliant in all areas. Cure & Seal 30% J23WB cures, seals and dustproofs freshly finished concrete surfaces.

USE

Cure & Seal 30% J23WB is designed to be used on freshly finished concrete and surpasses the requirements of ASTM C-309 and C-1315. Cure & Seal 30% J23WB can be used on both interior and exterior concrete surfaces.

FEATURES

- May Contribute to LEED credits
- Earth Friendly (EF), VOC < 100 g/L
- VOC Compliant in All Regions
- Ultra UV Stable, Non-yellowing
- Attractive Gloss Finish
- Cures/Seals/Dustproofs New Concrete
- Low Odor
- Non-Flammable
- Safe to Use and Store
- Meets ASTM C1315
- Tested and compliant per CDPH V1.2



PROPERTIES

ASTM C-1315, Type 1 Class A
 ASTM C-309, Type I Classes A & B
 AASHTO M-148, Type 1, Classes A & B

Drying time:

Approximately 2-3 hours at 70°F (21°C) for recoating or light traffic.
 Wait 12 hours for heavy traffic.
 Dry time is temperature, wind and humidity dependent.

VOC

VOC < 100 g/L. Compliant with all Canadian and U.S. VOC regulations including Federal EPA, OTC, LADCO, SCAQMD & CARB.

Estimating Guide

Coverage Rates:

1st coat 200 – 400 Ft²/Gallon 4.9 – 9.8 M²/Liter
 2nd coat 400 – 600 Ft²/Gallon 9.8 – 14.8 M²/Liter

Texture and absorption rate of the concrete will influence coverage rate.

Packaging

PRODUCT CODE	PACKAGE	SIZE	
		Gallons	Liters
308669	Pail	5	18.9
308670	Drum	55	208.2
100329	Tote	275	1041

STORAGE

The Cure & Seal 30% J23WB should be stored in tightly sealed original factory containers. Store in a horizontal position to prevent moisture accumulation on the drum head. Do not allow to freeze. Shelf life of properly stored, unopened containers is 18 months.

Mixing

Stir thoroughly prior to use. Do not thin or dilute.

Placement:

Apply Cure & Seal 30% J23WB immediately after all surface water has disappeared and surface cannot be marred. Application of Cure & Seal 30% J23WB too early or too late can affect the overall curing performance. Use low pressure spray, roller or brush. Apply uniformly without puddles. Multiple thin coats are preferable over heavy coats. For improved application consistency and reduction in labor, use the Dayton Spray-Pro (Item # 309233 or 309232) power spray system. Application of a second coat, after the first coat has dried will provide a longer lasting, higher gloss film with improved water retention properties.

CLEAN UP

Clean tools and equipment with clean water while product is still wet. Dried material may be removed with Green Bean Clean.

TECHNICAL DATA SHEET

LIMITATIONS**FOR PROFESSIONAL USE ONLY**

This product should not be used at temperatures below 40°F (4°C). Do not apply concrete or mortar toppings over sealed surfaces. Avoid spraying Cure & Seal 30% J23WB into joint prior to installation of sealant. May show rubber tire marks. Do not use high speed mixing equipment. Remove Cure & Seal 30% J23WB with Citrus Cleaner J48 or Green Bean Clean[®] before applying resinous (epoxy, polyester, urethanes, etc.) coatings. When moisture-sensitive flooring is to be applied to the concrete treated with this product first refer to ACI 302.2R

PRECAUTIONS**READ SDS PRIOR TO USING PRODUCT**

- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

MANUFACTURER

Dayton Superior Corporation
1125 Byers Road
Miamisburg, OH 45342
Customer Service: 888-977-9600
Technical Services: 877-266-7732
Website: www.daytonsuperior.com

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.