

TECHNICAL DATA SHEET

DESCRIPTION

Sure Inject J56 is a 100% solids, high modulus, moisture tolerant, low viscosity epoxy adhesive for gravity feed or pressure injection of cracks in concrete. Sure Inject J56 meets the requirements of ASTM C-881 and AASHTO M-235.

USE

The primary use of the Sure Inject J56 is for pressure injection and gravity feed crack repair in concrete and masonry. Sure Inject J56 can also be used to seal interior slabs and exterior above-grade slabs.

FEATURES

- High modulus, high strength adhesive
- Low viscosity, for deep penetration
- Moisture tolerant
- V.O.C. Compliant
- Packaged in cartridges and gallon units
- High chemical resistance

PROPERTIES

Meets ASTM C-881/ AASHTO M-235, Types I, II, IV, V, Grade 1, Classes B & C

Mix ratio: 2:1, Part A to Part B by volume

Color (mixed): Amber

Viscosity: 518 cps

Gel times: 60 gm mass - 28 Minutes @ 23°C

Final cure @ 7 days.

Compressive yield strength (ASTM D-695)
85.4 MPa @ 7 days

Compressive Modulus (ASTM D-695):
1845.0 MPa

Concrete bond strength (ASTM C-882)
2 days 16.4 MPa
14 days 29.2 MPa

Tensile Strength (ASTM D-638): 49.4 MPa

Elongation at break (ASTM D-638): 2.3%

Water Absorption (ASTM D-570): 0.84%

VOC

Sure Inject J56 has a VOC content of 0 g/L .
Compliant with all Canadian and U.S. VOC regulations including Federal EPA, OTC, LADCO, SCAQMD & CARB.

Packaging

PRODUCT CODE	PACKAGE	SIZE
307510AU	Cartridge	400 ml
307509AU	Unit	11.36 liters

STORAGE

The material should be stored at 5°-35°C. Shelf life of properly stored, unopened containers is 24 months and 12 months for cartridges.

APPLICATION

Surface Preparation:

Cracks to be bonded must be clean and sound. Remove all dirt, grease, oil, and other foreign material that may prevent a good bond. The crack may be damp or dry, but free of standing water. Use clean, oil free, compressed air to blow out any remaining dust or debris prior to installation. Air, material, and surface temperature must be 5°C and rising prior to mixing or installation.

Mixing:

Condition material to 18°- 29°C before using. Premix each component separately then mix two parts by volume of Part A with one part by volume of Part B for three minutes with a low speed (< 450 rpm) drill using a jiffy mixer or paddle. Mix only as much material as can be used within the pot life.

Placement:

For pressure injection, first prepare the surfaces adjacent to the cracks to expose clean, sound concrete. The injection ports should be spaced from 20.3 cm to 91.4 cm apart depending on the crack width and the thickness of the member to be injected. Next, the crack should be sealed at the surface with Sure Anchor™ epoxy gel J50 or J51. After the Sure-Anchor epoxy gel has cured, inject Sure Inject J56 with pressurized dispensing equipment or use cartridges from Dayton Superior. Do not install ports at the extremities of fine cracks as they feather to disappearance, install a terminal port approximately 10.16 cm from the end. Narrow cracks fill quicker from a wider adjacent crack segment than from a surface port. Sure Inject J56 cartridges are only designed for small repair projects with cracks at least 1.6 mm in width or larger. For large projects and/or crack widths less than 1.6mm, use Sure Inject J56 in 11.36 L units with pressurized dispensing equipment. For sealing slabs, spread the Sure Inject J56 over the interior slab or above grade exterior slab. Allow material to penetrate then remove any excess material to prevent the formation of a surface film.

CLEAN UP

Tools and Equipment: Clean before the epoxy sets up. Use Xylene or Dayton Superior Citrus Cleaner J48.

LIMITATIONS

FOR PROFESSIONAL USE ONLY

Minimum age of concrete must be 21-28 days from date of placement depending on curing and drying conditions. Always test a small amount to insure that the product is mixed properly and thoroughly and that the material will harden properly before proceeding with the installation

TECHNICAL DATA SHEET

Do not inject cracks wider than 6.4 mm without contacting Dayton Superior
At the completion of each project, it is recommended to take core samples to verify the satisfactory penetration of Sure Inject J56 epoxy into the crack
Do not thin with any solvents
Surface, ambient and material temperatures must be 5°C or above
Do not expose stored or uncured product to cold or freezing temperatures below 2°C for any length of time

Note: High temperatures will accelerate the setting time. As a general rule, the gel time of the epoxy will be cut in half for each 10° to 15° increase in temperature above 24°C.

PRECAUTIONS**READ SDS PRIOR TO USING PRODUCT**

- Component A – Irritant
- Component B – Corrosive
- Product is a strong sensitizer
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements
- Cured epoxy resins are innocuous

MANUFACTURER

Dayton Superior Corporation (Australia) PTY LTD
Suite 2201 Level 22 Tower 2
Westfield Bondi Junction
101 Grafton Street
Bondi Junction NSW 2022
Australia Phone: +61 (0)2 8095 6372
Fax: +61 (0)2 8095 6363
Website: www.daytonsuperior.com.au

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.