

TECHNICAL DATA SHEET

DESCRIPTION

Sure Lift with Dye J6D is a solvent based reactive and membrane forming cure and bond breaker for use in tilt wall construction. Sure Lift with Dye J6D is a special formula of polymers and propriety ingredients designed to provide clean, easy lifting of tilt panels. Sure Lift with Dye J6D has a fugitive dye for ease of visual inspection during application.

Also available without dye, Sure Lift J6 clear.

USE

Sure Lift with Dye J6D is designed to allow for easy lifting of tilt wall panels from properly designed, finished and cured concrete casting beds.

FEATURES

- Chemically reactive
- Good resistance to rain and weather
- Panels lift cleanly
- Minimal panel residue
- Resists construction foot traffic
- Meets the moisture retention properties of ASTM C 309 when applied to a steel troweled surface.

Drying time:

Approximately 2 hours at 70°F (21°C). Cooler temperatures higher humidity and thicker bond breaker coats will extend the dry time.

Note:

Prior to application, read, and follow all current (verify literature is current) literature instructions, limitations, The instructions provided by this technical data sheet apply to general average site conditions such as concrete mix designs, finishing techniques, and site ambient conditions.

Estimating Guide

Cure Coat: 100*-200 sq. ft./gal (2.4, 4.9 sq. M/L)
* meets ASTM C 309 moisture retention requirements on a steel troweled surface.

Bond Breaker Coats:

First Coat: 400 sq.ft./gal.(9.8 sq.M/L)

Second Coat: 550-700 sq.ft./gal(13.5-17.2 sq.M/L). The above recommended coverage rates are averages based on average site and concrete conditions.

Complete and uniform coverage of the casting slab varies considerably with variations in the placing, curing, concrete mix design, density, finishing, and site specific ambient conditions.

It is not possible for the recommendations provided by this data sheet to accommodate and account for all variables associated with the coverage rate and application of the bond breaker. It is the contractor's responsibility to verify that the applied coverage rates and overall application of the bond breaker is in accordance with the specific site variables and conditions.

Packaging

PRODUCT CODE	PACKAGE	SIZE
69231AU	Drum	208.20 Liters
69233AU	Pail	18.9 Liters

STORAGE

The Sure Lift with Dye J6D should be stored in a tightly secured original factory container. Store in the horizontal position to prevent moisture accumulation on the drum head. Do not store below 0°F (-17.8°C). Shelf life in unopened containers is 24 months from the date of manufacture.

Surface Preparation:

The casting bed should be free of all foreign material, salts, laitance and the Sure Lift with Dye J6D protected, while drying, from all contaminants or particulate matter (i.e., dust, dirt and the like).

Spray equipment:

The Sure Lift™ with Dye J6D bond breaker must be applied by a high quality "low-pressure pump-up type sprayer" such as manufactured by Hudson, Chapin or others. The tip size must be able to produce a well atomized spray pattern. The sprayer must be kept under sufficient pressure to correctly atomize the Sure Lift™ with Dye J6D without streaming, tailing, or spitting. A 1/2 (0.5) gal. /minute tip is generally recommended for most applications. The use of an improper sprayer, a dirty sprayer, lower than adequate pressures or wrong tip can result in an uneven application, and either over or under application.

Cure Coat:

Concrete casting slabs must be smooth, dense, sound, of adequate thickness, and well cured. Improper or inadequate curing or finishing will increase slab permeability and decrease bond breaker effectiveness.

TECHNICAL DATA SHEET

It is recommended per ACI & ASTM to cure the concrete in accordance with ASTM C-309. Apply the cure application IMMEDIATELY after completion of troweling and final finishing and after the surface water has disappeared.

Cure Coat: Sure Lift™ with Dye J6D can be used for curing and meets ASTM C-309 when the proper coverage rates are followed. It is recommended per ACI & ASTM to cure the concrete in accordance with ASTM C-309. The use of Cure & Seal 25% J22UV or Cure & Seal LV 25% J20UV or other approved Dayton Superior solvent-based curing compound meeting ASTM C-309 can be used, see TDS for recommended application rates.

When using a Dayton Superior solvent-based cure and seal, apply per the products directions. Contact Dayton Superior Technical Services for additional information and recommendations.

Special Note: Curing membranes must be allowed to fully dry prior to application of the bondbreaker coats.

First Bond Breaker Coat:

Just prior to placing the reinforcing steel, and within two weeks of pouring the panels, spray apply the first bond breaker application of Sure Lift™ with Dye J6D at 400 sq. ft./gal. (9.8 sq m/L) to the point of rejection.

Spray at right angles to curing compound spray pattern. Specific site conditions may dictate coverage rates other than the normal recommended coverage rates. Adjust the actual applied rates accordingly.

Second Bond Breaker Coat:

Wait until first coat dries, approximately 2 hours depending on temperature and humidity, and apply a second coat at right angles to the previous coat. Coverage for the second coat will typically be 550 to 700 sq. ft./gal. (13.5-17.2 sq m/L). If light or white spots appear within 10-40 minutes after spraying, those areas are extra porous and should be fogged with water followed by a reapplication of the Sure Lift™ with Dye J6D at 550 to 700 sq. ft./gal. (13.5-17.2 sq m/L). Specific site conditions may dictate coverage rates other than the normal recommended coverage rates. Adjust the actual applied rates accordingly.

The number of bond breaker coats and coverage rates necessary to achieve a complete uniform coverage is highly dependent on the concrete casting slab mix design as well as its inherent porosity, finishing techniques, and other related site specific ambient conditions. Adequate bond breaker application is in large part dependent upon development of a uniform soap like feel of the bond breaker treated surface as well as beading of water. Bond breaker can also be checked by rolling up a small ball like amount under thumb pressure.

Extremely porous or rough casting slabs will necessitate successive additional coats of bond breaker to achieve a consistent uniform membrane of the correct coverage rate and membrane thickness. Extremely porous or otherwise absorptive slabs can also be fogged with water to a saturated surface dry (SSD) condition prior to application of bond breaker.

BOND BREAKER TEST

To verify the integrity of the bond breaker coat, sprinkle water on the casting bed. (Water should bead up as on a freshly waxed automobile). The applied, dried material should have a soap like feel, uniformly over the substrate. The application should appear uniform and continuous, with light areas requiring re-application. Failure to verify proper uniform application and coverage rates can result in panel sticking.

Testing must be performed over a large enough surface area in an adequate testing frequency to provide accurate and meaningful results.

It is entirely the contractor's responsibility to verify that the bond breaker has been evenly and uniformly applied at the recommended application/coverage rates given the various concrete mix design, densities, finishes, and porosity conditions on each project.

TECHNICAL DATA SHEET

HOT WEATHER PROCEDURES

In hot weather, the casting slab must be flooded with water to reduce its porosity and cool it down prior to the first bond breaker application of Sure Lift™ with Dye J6D. Thoroughly saturate the slab with water, and then squeegee off the excess, removing all the free standing water from the surface, then immediately proceed with applying the first application of the Sure Lift™ with Dye J6D. Delaying the application of the bond breaker after wetting of the slab will result in over penetration and lessen bond breaker effectiveness and panel sticking may result. Prior to concrete placement wet down the casting slab with cool water; excessive water should be blown out immediately prior to the concrete placement. Take care when placing concrete to avoid abrading or scouring the bond breaker on the casting bed as braded or scoured spots or areas may result in stuck panels. Discharge the concrete into previously placed fresh concrete.

CLEAN UP

Tools and equipment, use mineral spirits, naphtha or xylol.

LIMITATIONS

FOR PROFESSIONAL USE ONLY

Avoid contamination by storing containers in clean, dry area and keeping lids tightly sealed when properly stored.

Do not spray on reinforcing steel. Not recommended for application to broom finished or otherwise rough, porous or weak unsound concrete.

Do not apply in rain or if rain is forecast within 12 hours of the application. Casting slab surfaces exposed to rain may require reapplication of the bond breaker at a coverage rate at 550-700 sq. ft./gal (13.5-17.2 sq. M/L). Do not apply below 40°F (4°C) or when ambient temperatures are expected to fall below 40°F (4°C) within 12 hours.

Not recommended for application to casting slab concrete that has been cured with curing blankets or plastic coverings without first removing the salts from the concrete's surface before application of the bond breaker. Surface salts can result in surface defects.

Application of the bond breaker as a cure coat during cool weather or when a moisture barrier has been used will result in longer than normal drying times. Application in two thin coats rather than one thick coat will reduce the dry time.

Properly applied, casting beds and tilt panels can normally be coated or sealed after appropriate cleaning and or surface preparation of the surfaces. The manufacture of the coating, paint, sealer, adhesive or other subsequent treatments should be consulted for specific substrate cleaning and preparation requirements and instructions prior to painting. The Tilt-Up Concrete Association (TCA) Tilt Tips "Painting Tilt-Up Panels" document should be understood and followed if painting of the tilt panels is anticipated.

Over-application can lead to excessive transfer to the panels and potentially cause problems with subsequent paint adhesion. A mock-up test panel of any subsequent application of paint/coatings or other membrane forming treatments should always be applied and tested to verify proper coating adhesion and adequate cleaning and surface preparation of the tilt panels. Improper concrete mix designs, overly porous or weak casting slab concrete, failure to properly finish and/or cure the concrete and/or uneven or improper application and insufficient mixing of the bond breaker can lead to panel sticking.

PRECAUTIONS

READ SDS PRIOR TO USING PRODUCT

- Keep material and containers away from high heat, open flames, sparks or other sources of ignition
- Use with adequate ventilation
- Wear protective clothing, gloves and eye protection (goggles, safety glasses and/or face shield)
- Keep out of the reach of children
- Do not take internally
- In case of ingestion, seek medical help immediately
- May cause skin irritation upon contact, especially prolonged or repeated. If skin contact occurs, wash immediately with soap and water and seek medical help as needed.
- If eye contact occurs, flush immediately with clean water and seek medical help as needed
- Dispose of waste material in accordance with federal, state and local requirements

TECHNICAL DATA SHEET

MANUFACTURER

Dayton Superior Corporation (Australia) PTY LTD
31 Metrolink Circuit
Campbellfield, VIC 3061
Australia
Australia Phone: +61 1300 DAYTON (329866)
Website: www.daytonsuperior.com.au

WARRANTY

Dayton Superior Corporation ("Dayton") warrants for 12 months from the date of manufacture or for the duration of the published product shelf life, whichever is less, that at the time of shipment by Dayton, the product is free of manufacturing defects and conforms to Dayton's product properties in force on the date of acceptance by Dayton of the order. Dayton shall only be liable under this warranty if the product has been applied, used, and stored in accordance with Dayton's instructions, especially surface preparation and installation, in force on the date of acceptance by Dayton of the order. The purchaser must examine the product when received and promptly notify Dayton in writing of any non-conformity before the product is used and no later than 30 days after such non-conformity is first discovered. If Dayton, in its sole discretion, determines that the product breached the above warranty, it will, in its sole discretion, replace the non-conforming product, refund the purchase price or issue a credit in the amount of the purchase price. This is the sole and exclusive remedy for breach of this warranty. Only a Dayton officer is authorized to modify this warranty. The information in this data sheet supersedes all other sales information received by the customer during the sales process. THE FOREGOING WARRANTY SHALL BE EXCLUSIVE AND IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES OTHERWISE ARISING BY OPERATION OF LAW, COURSE OF DEALING, CUSTOM, TRADE OR OTHERWISE.

Dayton shall not be liable in contract or in tort (including, without limitation, negligence, strict liability or otherwise) for loss of sales, revenues or profits; cost of capital or funds; business interruption or cost of downtime, loss of use, damage to or loss of use of other property (real or personal); failure to realize expected savings; frustration of economic or business expectations; claims by third parties (other than for bodily injury), or economic losses of any kind; or for any special, incidental, indirect, consequential, punitive or exemplary damages arising in any way out of the performance of, or failure to perform, its obligations under any contract for sale of product, even if Dayton could foresee or has been advised of the possibility of such damages. The Parties expressly agree that these limitations on damages are allocations of risk constituting, in part, the consideration for this contract, and also that such limitations shall survive the determination of any court of competent jurisdiction that any remedy provided in these terms or available at law fails of its essential purpose.