



TECHNICAL DATA SHEET

AquaFlash® System

A Liquid-Applied Transition Membrane
for Sealing Rough Openings at Windows,
Doors and Other Wall Penetrations
DS494

PRODUCT DESCRIPTION

AquaFlash Liquid is an extremely flexible, water-based polymer material used in conjunction with AquaFlash Mesh and AquaFlash Corners, non-woven blend fabric, to seal substrates around windows, doors and other openings.



BASIC USES

The AquaFlash System provides an effective, water-resistant transition membrane to provide continuity of Dryvit's Backstop® NT™ air and water-resistive barrier between different substrate materials and to bridge across sheathing joints, at openings, at inside and outside corners, as well as across floor lines.

FEATURES & BENEFITS

FEATURE

- Fluid-applied technology
- Single component
- Waterproof

BENEFIT

- Easy to use
- Ready to use
- Meets AC148 criteria as a flashing membrane

PROPERTIES

Benefits: AquaFlash Liquid is used directly from the pail and can be applied using a brush or roller over approved, clean, dry substrates. When applied in accordance with Dryvit recommendations, AquaFlash System can be exposed to weather longer than conventional flashing tape prior to covering with a building cladding or siding. It is easy to apply and fully compatible with Dryvit's Backstop® NT™ as well as all Dryvit adhesives. AquaFlash Corners are designed to be used to reinforce window corners without the need for field cutting and forming.

Working Time: AquaFlash Liquid provides a working time similar to paint. The product will not set-up in the pail. Keep unused material covered to prevent evaporation. Any surface skin should be removed prior to use.

Drying Time: The drying time of AquaFlash System is dependent upon the air temperature, wind conditions and relative humidity. Under average drying conditions [70 °F (21 °C), 55% R.H.], AquaFlash System will be dry in approximately 30 minutes on absorbent substrates and 1 1/2 hours on non-absorbent substrates.

Performance Requirements: The AquaFlash System has been evaluated in accordance with ICC ES AC148 Acceptance Criteria for Flashing Materials (Self-adhering Flashing) as follows:

- **Tensile Strength:** (ASTM D 5034 and AC148 Sec. 4.1) - Minimum 39.9 lb/in (7.1 kg/cm) for aged specimen.
- **Nail Sealability:** (ASTM D 1970 and AC148 Sec. 4.2) - No water penetration.
- **Accelerated Aging Prior to Peel Adhesion:** (AC148 Sec. 4.3.1.1.1) -25 cycles: 3 hrs at 120 °F (49 °C), 3 hrs water immersion, 18 hrs at -40 °F (-40 °C). No visible damage under 5x magnification.
- **Peel Adhesion:** (ASTM D3330 and AC148 Sec. 4.3) – Peel strength of aged specimens exceeded 75% of control specimens.
- **Ultraviolet Exposure:** (AC148 Sec. 4.4) - 210 hrs - No deleterious effects when viewed under 5x magnification.
- **Accelerated Aging Prior to Water Resistance:** (AC148 Sec. 4.5.2.2) - 25 cycles: 3 hrs at 120 °F (49 °C), 3 hrs water immersion, 18 hrs air dry: No visible damage under 5x magnification.

- **Water Resistance:** (AATCC Method 127 and AC148 Sec. 4.5) – No water leakage after UV exposure and accelerated aging cycling.
- **Pliability:** (AC148 Sec. 4.6) - No cracking when bent over 1/8 in (3 mm) mandrel at 32 °F (0 °C).

Acceptable Substrates:

- Exterior grade gypsum sheathing meeting ASTM C 1396 (formerly C 79) requirements for water resistant core or Type X core at the time of application
- Exterior sheathing having a water-resistant core with fiberglass mat facers meeting ASTM C 1177
- Exterior fiber reinforced cement or calcium silicate boards
- APA Exterior or Exposure 1 Rated Plywood, Grade C-D or better, nominal 1/2 in (12.7 mm), minimum, installed with the C face out
- APA Exterior or Exposure 1 Fire Retardant Treated Plywood, Grade C-D or better, nominal 1/2 in (12.7 mm), minimum, installed with the C face out
- APA Exposure 1 Rated Oriented Strand Board (OSB) nominal 1/2 in (12.7 mm), minimum
- Unpainted, unsealed concrete and CMU
- Galvanized metal and aluminum

Job Conditions: Air and substrate temperature for application of AquaFlash System must be 40 °F (40 °C) minimum to 100 °F (38 °C) maximum and must remain so for a minimum of 12 hours or until dry. Cool, damp conditions may require longer drying time. Temporary protection shall be provided at all times until membrane, adhesive, base coat, finish and permanent flashings, sealants, etc. are completed to protect the wall from weather and other damage.

SURFACE PREPARATION

Substrate surfaces shall be sound, dry and free of foreign materials such as dirt, dust, oil, paint, wax, water repellants or other materials that inhibit adhesion. The AquaFlash System can bridge substrate gaps up to 1/4 in (6.4 mm). Larger gaps may require special treatment.

MIXING

AquaFlash Liquid is ready for use after an initial spin-up using a drill with paddle mixer. **DO NOT ADD CEMENT OR ANY OTHER ADDITIVES.**

APPLICATION

Using a brush or 3/4 in (19 mm) nap roller, apply a liberal coat of AquaFlash Liquid material to the substrate surface. Immediately embed the AquaFlash Mesh or AquaFlash Corners into the wet material. Add additional AquaFlash Liquid material and smooth out to remove any wrinkles and fully embed the mesh. Allow to set for a minimum of 15 minutes, apply a second liberal coat of AquaFlash Liquid and smooth out to ensure a uniform continuous film free of voids, pinholes or other discontinuities. Joints in the AquaFlash mesh should overlap a minimum of 2 in (51 mm).

COVERAGE AND PACKAGING

AquaFlash Liquid: Material is supplied in 8 lb (3.6 kg) or 40 lb (18.2 kg) containers. See table below for coverage.

All coverages are approximate and depend upon substrate, details and individual application technique.

4" MESH	6" MESH	9" MESH
38 lf/lb (25.5 m/kg)	25 lf/lb (16.8 m/kg)	17 lf/lb (11.42 m/kg)

AquaFlash Mesh: The mesh is available in both rolls and prefabricated corner pieces. Each roll is 180 lf (54.9 m) in length and packaged as follows:

4 in (102 mm): 9 rolls/box

6 in (152 mm): 6 rolls/box

9 in (229 mm): 4 rolls/box

The AquaFlash Corners are available in 6 in (152.4 mm) widths (152 mm) and packaged 100/box.

STORAGE

AquaFlash Liquid shall be stored at a minimum of 40 °F (40 °C) and a maximum of 100 °F (38 °C) in tightly sealed containers protected from weather and out of direct sunlight. The shelf life is 2 years from date of manufacture when properly stored in unopened pails.

CAUTIONS & LIMITATIONS

- Avoid applying AquaFlash System in direct sunlight. Always work on the shady side of the wall or protect the area with appropriate shading material.
- Apply the AquaFlash System to acceptable substrates only.

CLEAN UP

Clean tools with water while AquaFlash Liquid is still wet.

TECHNICAL AND FIELD SERVICES

Available on request.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 1.1.2022

©Dryvit 2022

DS494

Tremco Construction Products Group (CPG) brings together the Commercial Sealants & Waterproofing and Roofing & Building Maintenance divisions of Tremco CPG Inc.; Dryvit and Willseal brands; Nudura Inc.; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc.; Weatherproofing Technologies Canada, Inc.; and Pure Air Control Services, Inc.



dryvit.com | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com