




TECHNICAL DATA SHEET

FERROS™ FINISH FERROS™ Primer 1200

Exterior and Interior Decorative
Finish and Primer DS884

PRODUCT DESCRIPTION



Ferros finish provides a modern and elegant look for either interior or exterior applications. The final appearance replicates the well-known effect of rusting metal or steel with distinct oxidations. In addition to its unique appearance, Ferros finish is water-based and has hydrophobic qualities that repel liquids and contaminants. Ferros finish forms a breathable film having excellent resistance to abrasion and long term weathering.

FEATURES & BENEFITS

FEATURE

- Hydrophobic chemistry
- Available in 4 colors and 2 textures

FEATURE

- Hydrophobic chemistry
- Available in 4 colors and 2 textures

PROPERTIES

Approved Substrates:

Interior: Ferros finish may be applied over most common interior building materials including properly prepared and primed gypsum wallboard, cement board, plaster, concrete and masonry. Surface quality of the substrates before application should be equal to a Level 4 drywall finish or better.

Exterior: Ferros finish can be applied over properly prepared and primed exterior cement plaster, concrete, metal, masonry and a Dryvit base coat.

Testing Information: For individual test data on this product's properties, refer to the chart included within this document.

SURFACE PREPARATION

Surfaces to receive Ferros finish shall be clean, dry, and smooth, equivalent to Level 4 drywall.

APPLICATION

General: Simply stir by hand and start applying per the instructions and application video on our website. To create the colors displayed in the catalog, apply by either trowel or brush as detailed in the application video. Use of Ferros Primer 1200 series is required to duplicate the catalog samples and achieve product performance.

Ferros Primer 1200 Application:

- Dilution: 10 – 15% with water
- Application Temperature: 40 - 90 °F (4 - 32 °C)
- Shelf Life: 24 months in unopened and properly stored containers.
- Overpainting: 4 - 6 hours
- Method of Primer Application: Roller, brush or spray. Apply in 1 or 2 coats as needed to achieve 100% uniform coverage of substrate.

Ferros Finish Application:

Ferros has two different finish effects, **troweled** and **dripping**. Select your desired finish option effect before you begin application of the finish. Hand stir the finish before using.

- Dilution: do not dilute.
- Color: rusted metallic
- Temperature: 50 - 80 °F (10 - 27 °C).
- Shelf Life: 12 months in unopened, properly stored containers.
- Number of Coats: 1 or 2, depending upon desired appearance and performance.
- Overcoating: 3 - 4 hours
- Method of Application: Brush or trowel. Apply in 1 or 2 coats as needed. **DO NOT** apply to hot surfaces or in direct sunlight, as it is necessary to keep the finish open to manipulate the effect. Protect applied finish for 24 hours from water (rain or fog) and from touch.

Troweled Effect: Using a stainless-steel trowel, apply one coat of Ferros finish to fully cover the surface, applying strokes in all directions to leave a layer of finish approximately 8 - 10 mils thick.

Coverage: 1.1 qt (1 L) of Ferros finish for approximately 21 - 31 ft² (2 - 3 m²), 5.3 qt (5 L) for approximately 105 – 155 (10 - 15 m²). 1 coat on smooth surfaces.

Dripping Effect: With the narrow side of a 5 in (25 mm) block brush, apply one coat of Ferros finish from top to bottom and vice-versa, leaving jagged streaks 0.04 - 0.4 in (1 – 20 mm) wide and 0.04 – 0.08 in (1 – 2 mm) thick. See photo for the proper type of block brush. After 15 - 20 minutes at 70 °F (20 °C), apply a second coat using a stainless-steel trowel and spread the finish vertically from top to bottom and vice versa, leaving a layer of paint approximately 4 - 5 mils thick. Smooth the surface vertically with a dry trowel while taking care not to remove Ferros material. It is important to apply the product wet-on-wet and avoid letting it dry, especially along the joints.

Coverage: 1.1 qt (1 L) approximately 15 - 22 ft² (1.4 - 2 m²), 5.3 qt (5 L) approximately 75 - 110 ft² (7 - 10 m²). 2 coats on smooth surfaces.

VOC CONTENT

Primer 1200 27 g/l

Ferros finish 10 g/l

FERROS FINISH TESTING

TEST	TEST METHOD	RESULTS
Accelerated Weathering	ASTM G154	2000 hr - No deleterious results
Water Vapor Transmission	ASTM E96 Procedure B	19.8 Perms
Tensile Bond Strength	UNI EN 1542:2000	194 psi (1.34 N/mm ²)
Porosity	UNI EN 1062-3:2008	<.018 psf / h1/2(<0.09 Kg/m ² * h1/2)
Fungal Resistance	UNI EN 15457:2014	21 days - No growth
Algae Resistance	UNI EN 15458:1014	28 days – No growth

COVERAGE AND PACKAGING

Ferros finish is available in 1.1 qt and 5.3 qt (1 L and 5 L) pails. One 5.3 qt (5 L) pail of Ferros finish covers approximately 130 ft² (12 m²) of finished wall. Ferros Primer 1200 is available in both a 1.1 qt (1 L) pail and covers approximately 99 ft² (9.2 m²) and

a 5.3 qt (5 L) pail covering approximately 495 ft² (46.4 m²). Coverage will vary according to the smoothness of the substrate, surface absorption and application method.

DESIGN OPTIONS

Available in 4 color variations:

COLORS	FERROS PRIMER 1200
100RIF	White Primer
101RIF	Gray Primer
102RIF	Gray Primer
105RIF	Gray Primer

Available in 2 effects:

Troweled: Using a stainless-steel trowel, the material is spread and smoothed across the surface.

Dripping: This effect is achieved by dripping the material in vertical motions using a brush or block brush stroking in vertical lines.

Ferros materials are fully pigmented and ready to apply.

Refer to the Ferros application video at the link below for complete application instructions.

https://www.youtube.com/embed/_4f274nyReM

DELIVERY TIME

Stock item ready to ship.

CLEAN UP

Clean brushes, rollers, tool, and equipment with soap and warm water immediately after use. Do not reuse containers and properly dispose of empty containers.

HANDLING & STORAGE

Close all containers tightly when not in use. Store in a cool dry place away from direct sunlight. **Protect from freezing. Protect from heat over 100 °F (38 °C).** Stack to maximum of three (3) pails high. Ferros finish and Ferros Primer 1200 has a one (1) year shelf life in unopened, properly stored containers

DISPOSAL

Dispose of unused or unwanted product in accordance with local laws regulating water-based coatings.

Information contained in this product sheet conforms to the standard detail recommendations and specifications for the installation of Dryvit products as of the date of publication of this document and is presented in good faith. Dryvit assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Dryvit.

For more information on Dryvit or Continuous Insulation, [click here](#).

Printed in USA. Issued 1.1.2022

©Dryvit 2022

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



dryvit.com | 800.556.7752



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com